Online Research @ Cardiff

This is an Open Access document downloaded from ORCA, Cardiff University's institutional repository: <https://orca.cardiff.ac.uk/id/eprint/121183/>

This is the author's version of a work that was submitted to / accepted for publication.

Citation for final published version:

Lang, Lin Zhi, Tripathy, Snehasis ORCID: <https://orcid.org/0000-0003-1632-7668>, Baille, Wiebke, Schanz, Tom and Sridharan, Asuri 2019. Linkage between swelling pressure, total suction of saturated bentonites and suction of saturating aqueous solutions. Applied Clay Science 171 , pp. 82-91. 10.1016/j.clay.2019.02.007 file

Publishers page: <http://dx.doi.org/10.1016/j.clay.2019.02.007>
<<http://dx.doi.org/10.1016/j.clay.2019.02.007>>

Please note:

Changes made as a result of publishing processes such as copy-editing, formatting and page numbers may not be reflected in this version. For the definitive version of this publication, please refer to the published source. You are advised to consult the publisher's version if you wish to cite this paper.

This version is being made available in accordance with publisher policies.

See

<http://orca.cf.ac.uk/policies.html> for usage policies. Copyright and moral rights for publications made available in ORCA are retained by the copyright holders.

1 **Linkage between swelling pressure, total suction of**
2 **saturated bentonites and suction of saturating aqueous**
3 **solutions**

4 L.Z. Lang^{1*}, S. Tripathy², W. Baille¹, T. Schanz^{1,†} and A. Sridharan³

5 1 Department of Civil and Environmental Engineering, Ruhr-Universität Bochum, Germany

6 2 Geoenvironmental Research Centre, School of Engineering, Cardiff University, UK

7 3 Indian National Science Academy, India

8 *Corresponding author. E-mail address: Linzhi.Lang@rub.de

9 † Deceased 12 October 2017

10 **Abstract:** In deep geological repositories, compacted bentonites have been proposed
11 for use as barrier materials for isolating nuclear waste. The prevailing hydro-mechanical-
12 chemical boundary conditions in the repositories can affect the swelling capacity of compacted
13 bentonites. The present study examines the linkage between the swelling pressure of saturated
14 bentonites, the total suction of saturated bentonites and the suction of hydrating fluids. An
15 equation describing the linkage between these parameters was derived based on the thermo-
16 dynamics of soil moisture. To validate the derived relationship, laboratory tests involving
17 constant volume swelling pressure tests and total suction measurements after the swelling
18 pressure tests were carried out on a selected Ca-Mg-rich bentonite. Seven bentonite samples
19 with compaction dry density ranging from 1.20 and 1.83 Mg/m³ were hydrated with deionized
20 water, whereas four samples with a dry density of 1.59 Mg/m³ were hydrated with 0.0001 to
21 2.0 M CaCl₂ solutions. The total suctions of the saturated bentonite and the hydrating fluids
22 were determined by using a chilled-mirror hygrometer. The total suction of the saturated ben-
23 tonite was found to be affected by the compaction dry density and the suction of the hydrating
24 fluids. The experimental results from the present study and from the literature demonstrated
25 that the total suction of saturated bentonites minus the suction of the hydrating fluid used to
26 saturate bentonites is approximately equal to the swelling pressure of saturated bentonites.

27 **Keywords:** Expansive soils; bentonite; swelling pressure; suction; thermodynamics of soil
28 moisture; radioactive waste disposal

29 1. Introduction

30 A deep geological repository for the disposal of high-level radioactive wastes (HLWs)
31 may be located either in crystalline rock, argillaceous rock, or even in salt rock. The HLW
32 canisters isolated by compacted bentonites are planned to be placed in the disposal boreholes
33 located at a depth of 300 to 1000 m, depending on the disposal concepts (Pusch and Yong,
34 2006). Compacted bentonites are expected to swell upon imbibing groundwater thereby filling
35 the construction gaps and finally exerting a pressure on the host rock. Under this confined
36 condition and given the high installation dry densities, the swollen bentonites would possess
37 low porosity and low hydraulic conductivity. The saturated bentonite barriers are expected
38 to adsorb the positively charged radioisotopes from the HLWs and retard their migration to
39 the geosphere (Bergaya et al., 2006).

40 The swelling pressure of compacted bentonites has been considered as an important
41 mechanical parameter for assessing the long-term stability of the barrier in deep geological
42 repositories. From the perspective of laboratory measurements, the swelling pressure can
43 be defined as the pressure required to hold a bentonite sample at constant volume when it
44 absorbs fluid and tends to swell. Several investigations in the past have shown that the solute
45 concentration in the hydrating fluid, compaction dry density, and properties of bentonites
46 affect the magnitude of swelling pressure and the water content at saturation (Pusch, 1980*b*;
47 Bucher and Max, 1989; Pusch et al., 1990; Komine and Ogata, 1996; Karnland et al., 2005;
48 Castellanos et al., 2008; Villar and Lloret, 2008*b*; Schanz and Tripathy, 2009; Zhu et al., 2013;
49 Yigzaw et al., 2016).

50 The total suction of unsaturated soils consists of matric and osmotic suctions (Yong
51 and Warkentin, 1975; Fredlund et al., 2012; Lu and Likos, 2004). In clays, the matric suction

52 is due to surface tension, adsorptive forces and osmotic forces (i.e. the diffuse double layer
53 forces), whereas the osmotic suction is due to the presence of dissolved solutes in the pore
54 water.

55 Following saturation of a compacted bentonite sample with deionized water, the matric
56 and the total suction of the sample are generally assumed to be nearly equal to zero (e.g.
57 Wang et al. (2012), Agus et al. (2013), Yigzaw et al. (2016), Măsin and Khalili (2016), among
58 others). Although the suction of deionized water is approximately equal to zero, however,
59 the assumptions with regard to a zero matric suction and a zero total suction in case of
60 saturated bentonites may not be considered appropriate. Fredlund et al. (2012) stated that
61 even when a soil is saturated under positive pore-water pressure, the osmotic component of
62 the total suction still remains. Tripathy et al. (2014a) found that the calculated osmotic
63 suction in various bentonites increased from 2 MPa to more than 19 MPa during the drying
64 process, depending upon the nature of exchangeable cations and the water content. Total
65 suction measurements after constant volume swelling pressure tests on a Na-bentonite and on
66 sand-bentonite mixtures that were saturated with deionized water and salt solutions have been
67 reported by Karnland et al. (2005) and Arifin (2008), respectively. These studies demonstrated
68 that the total suctions after the release of confinement in Na-bentonite and sand-bentonite
69 mixtures can be several hundreds of kPa to ten of MPa. The studies above imply that the
70 type and amount of exchangeable cations and the water content or the swollen dry density
71 influence the total suction of saturated bentonites.

72 In addition to the water content, temperature and composition of the pore water, the
73 overburden pressure influences the swelling clay suction (Croney, 1952; Kassiff and Shalom,
74 1971; Towne, 1981). They stated that for saturated swelling clays, the overburden pressure
75 was equal to the sum of effective suction and pore water pressure. The effective suction is
76 the matric suction of an unloaded sample of the soil whose water content is the same as
77 that of a loaded sample. The pore water pressure is the pore pressure of the loaded sample.

78 Moreover, Lambe and Whitman (1969); Nagaraj et al. (1994); Singhal et al. (2015) indicated
79 that removing overburden pressure from clays can induce a negative pore water pressure or
80 capillary suction.

81 A review of the literature presented herein suggested that an interdependency between
82 the swelling pressure, the total suction and the suction of hydrating fluids are expected in
83 case of swelling clays. Karnland et al. (2005) indicated that for saturated Na-bentonite, the
84 swelling pressure was the difference of the potential pressure (total suction) and the external
85 osmotic pressure (suction of hydrating fluids). The theoretical linkage between the swelling
86 pressure, the total suction and the suction of the hydrating fluids introduced by Karnland
87 et al. (2005) was based on constant volume condition. However, the experimental validation
88 of their linkage corresponds to unconfined condition. The total suction determined after re-
89 leasing the confinement conditions may be due to a negative pore water pressure or capillary
90 suction induced by unloading (Lambe and Whitman, 1969; Nagaraj et al., 1994; Singhal et al.,
91 2015). According to the effective stress concept, unloading would induce a negative pore wa-
92 ter pressure or capillary suction. Moreover, no systematic studies were made in the past to
93 explore the linkage between the swelling pressure, the total suction of saturated Ca-bentonite
94 and the suction of saturating aqueous solutions. Therefore, it is of interest to systematically
95 study the linkage between swelling pressure, total suction of saturated bentonites and suction
96 of saturating aqueous solutions. Understanding of the linkage between the various relevant
97 parameters will enable researchers to develop models that will facilitate evaluating the influ-
98 ence of hydro-mechanical-chemical boundary conditions on the stability of the barrier in deep
99 geological repositories.

100 The objective of this study was to examine the linkage between the swelling pressure,
101 the total suction and the suction of hydrating fluids in case of saturated bentonites. An
102 equation describing the linkage between these three parameters was first derived based on
103 the thermodynamics of soil moisture. Further, constant volume swelling pressure tests and

total suction measurements after the swelling pressure tests were carried out on a selected bentonite. Based on the experimental results from this study and from the literature, the derived equation was then validated.

2. Theoretical considerations

Total potential of soil-water has been discussed from the point of view of thermodynamic considerations of soil moisture by numerous researchers (Edlefsen and Anderson, 1943; Low and Deming, 1953; Bolt and Miller, 1958; Mitchell, 1962; Yong and Warkentin, 1975; Iwata et al., 1995). Iwata et al. (1995) stated that the total water potential (μ) in clays relative to the potential of the free pure water at the same temperature and external pressure is comprised of the potentials due to surface tension (μ_c), van der Waals force (μ_f), solutes (μ_0), electric field (μ_e), temperature (μ_T), pressures (μ_P), and gravitational field (μ_g) (Eq. 1).

$$\mu = \mu_c + \mu_f + \mu_0 + \mu_e + \mu_T + \mu_P + \mu_g \quad (1)$$

Detailed description about these potentials could be found in the work of Iwata et al. (1995). Since μ_c , μ_f , μ_0 , μ_e and μ_P are the potentials which are closely related the discussion in this paper, their definitions are given in the following paragraphs.

Curved surfaces of water are formed in soils pores under unsaturated condition. The water menisci give rise to a decrease in the total potential of the water and this decrease is described by the surface tension effect or capillary potential (μ_c).

Van der Waals force effect (μ_f) corresponds to the potential energy of interaction between clay surface and a water molecule. Therefore, μ_f results in a decrease in the total potential of the water and the decrease in the total potential of soil water depends upon the distance from the surface of the clay particle to a water molecule.

Solute effect (μ_0) results from various solutes in the soil solution. The various solutes in the soil solution result in a decrease in the total potential of soil water and the decrease in

127 the total potential of soil water depends on the concentration of the various solutes in the soil
128 solution.

129 Clay minerals have electric charge and the soil solution is affected by the electric field
130 induced by those charges. The change of the total potential of water in soil because of electric
131 displacement is defined as μ_e .

132 To satisfy the requirement of equilibrium, the concept of the effect of pressures (μ_P)
133 is introduced. According to the thermodynamics of soil moisture, at equilibrium state, the
134 effect of pressures compensates for the drop in the total potential of the water near the clay
135 particle caused by surface tension, van der Waals force, solutes, electric field, temperature and
136 gravitational field.

137 The applicability of the potentials above can be examined in the light of a constant
138 volume swelling pressure test on compacted bentonite. Studies on the pore size distribution of
139 compacted bentonite-based materials have shown dual-structure pore size distributions with
140 inter-aggregate pores and intra-aggregate pores (Sridharan et al., 1971; Lloret et al., 2003;
141 Delage et al., 2006; Romero and Simms, 2008; Seiphoori et al., 2014). The inter-aggregate
142 pores and intra-aggregate pores are generally identified with macrostructural porosity and
143 microstructural porosity, respectively, when analysing compacted clays (Alonso et al., 1990;
144 Gens and Alonso, 1992; Musso et al., 2013; Manca et al., 2015; Navarro et al., 2017a, 2018).
145 Similarly, the total potential of macrostructural pore water (μ_M) and the total potential of
146 microstructural pore water (μ_m) have been considered in this work to analyse the constant
147 volume swelling pressure tests on compacted bentonite.

148 Sketches of a swelling pressure test device and of the structure of compacted bentonite
149 (macro and micro structure) are shown in Fig. 1. A compacted bentonite sample under
150 constant volume condition is hydrated with an aqueous solution. The upon saturation of the
151 sample in the measuring system (Fig. 1) during a swelling pressure test, the macrostructural
152 pores are filled with the aqueous solution. In addition, the microstructural pores are also filled

153 with water that may also include some solutes. At saturation, the water potential caused by
 154 surface tension (μ_c) gets eliminated. Considering that the temperature and the atmospheric
 155 pressure change little during an isothermal swelling pressure test, the potentials caused by
 156 temperature (μ_T) and atmospheric pressure can be neglected. Since the scale of this system
 157 is very small, it is reasonable to neglect the gravitational potential (μ_g). Therefore, the total
 158 potential of the macrostructural pore water (μ_M) would be reduced to only the potential due
 159 to solutes (μ_0^M) and is given by Eq. (2). In a swelling pressure test, μ_0^M corresponds to the
 160 total water potential of the hydrating fluid (μ_a). In suction terms, the total suction of the
 161 hydrating fluid is ψ_a . In Eq. (2), $\bar{v}_w$ is the partial specific volume of water.

$$\mu_M = \mu_a = -\psi_a \bar{v}_w \quad (2)$$

162 Similarly, the total potential of the microstructural pore water (μ_m) is given by Eq. (3). P
 163 is the pressure compensating for the drop in the total potential of the water near the clay
 164 particle due to van der Waals force, solutes and electric field and is approximately equal to
 165 net mean stress.

$$\mu_m = \mu_f^m + \mu_0^m + \mu_e^m + P\bar{v}_w \quad (3)$$

166 According to the thermodynamics of soil moisture, at equilibrium state, the total po-
 167 tential of the water at any given points in the system has a constant value. Thus, Eq. (4) can
 168 be obtained.

$$\mu_m = \mu_M \quad (4)$$

169 By rearranging Eqs. (2), (3), and (4), Eq. (5) can be obtained:

$$\mu_f^m + \mu_e^m + \mu_0^m = -\psi_a \bar{v}_w - P\bar{v}_w \quad (5)$$

170 It is generally assumed that $\bar{v}_w$ does not depend on pressure and is a constant, nearly $1 \text{ m}^3/\text{Mg}$.
 171 A simplification of Eq. (5) yields Eq. (6).

$$-\frac{1}{\bar{v}_w}(\mu_f^m + \mu_e^m + \mu_0^m) - \psi_a = P \quad (6)$$

172 Since $(\mu_f^m + \mu_e^m)$ and μ_0^m correspond to the hydration effect and osmotic effect, respec-
 173 tively, thus they correspond to matric potential and osmotic potential, respectively. Because
 174 $(\mu_f^m + \mu_e^m + \mu_0^m)$ corresponds to the sum of matric and osmotic potentials in case of saturated
 175 clays, their value can be approximately determined from Kelvin's equation (i.e. Eq. (7)).

$$\mu_f^m + \mu_e^m + \mu_0^m = \frac{RT}{M_w} \ln(RH) \quad (7)$$

176 In Eq. (7), R is the molar gas constant, M_w is the molecular mass of water, and RH is the
 177 relative humidity. In suction terms, the total suction (ψ_t) of the saturated bentonite under
 178 constant volume condition is given in Eq. (8)

$$\psi_t = -\frac{RT}{M_w \bar{v}_w} \ln(RH) \quad (8)$$

179 After Eqs. (6), (7), and (8) are combined, Eq. (9) can be obtained in suction and
 180 pressure terms, where P_s represents swelling pressure.

$$\psi_t - \psi_a = P = P_s \quad (9)$$

181 Croney (1952); Kassiff and Shalom (1971); Townenr (1981) suggested a similar relationship to
 182 Eq. (9) for a saturated clay under compression and no water content changes, i.e.

$$s + U = P \quad (10)$$

183 where s is the matric suction measured under zero load, corresponding to ψ_t in Eq. (9); U is
 184 the pore water pressure measured under load, corresponding to $-\psi_a$ in Eq. (9); P is the total
 185 external all-round pressure, corresponding to P_s in Eq. (9). If the aqueous solution in Fig. 1
 186 is pure water ($\psi_a = 0$), then Eq. (9) is reduced to the thermodynamic equations developed by
 187 Low and his co-workers (Low and Anderson, 1958; Viani et al., 1983; Low, 1987). In addition,
 188 similar expressions have been also given by Karnland et al. (2005) and Navarro et al. (2017a).

189 To validate Eq. (9) experimentally, separate measurements of P_s , ψ_a and ψ_t are neces-
 190 sary. The former two can be directly determined by a swelling pressure device and a chilled-
 191 mirror hygrometer, respectively. However, the latter cannot be directly determined by placing

192 a relative humidity sensor in a constant volume swelling pressure device. In constant volume
 193 condition, the water potential determined by the relative humidity sensor is the total water
 194 potential (μ_m or μ_M). This can be confirmed by constant volume infiltration experimental
 195 results reported by Cui et al. (2008); Ye et al. (2009); Mokni and Barnichon (2016); Villar
 196 et al. (2016). They found that the relative humidity above the wetting face reached nearly
 197 100% after long-term of supplying water. This indicates that the water potential determined
 198 by the relative humidity sensor in constant volume condition is equal to the water potential
 199 of the hydrating fluid (water). Thus, releasing swelling pressure by removing the confinement
 200 conditions is necessary for determining ψ_t or $(\mu_f^m + \mu_e^m + \mu_0^m)$.

201 If the hydrating fluid (Fig. 1) is removed before releasing the swelling pressure, subse-
 202 quent removal of swelling pressure can be considered as undrained unloading. Consequently,
 203 the water content of the saturated bentonite sample would not change after releasing the
 204 swelling pressure. Since μ_f^m and μ_e^m are dominated by water content or volume, it is reason-
 205 able to assume that they would not change after releasing the swelling pressure. Because μ_0^m
 206 is dominated by the molarity of solutes and the unloading does not change the mass of solutes
 207 and the water content, μ_0^m would remain after releasing the swelling pressure. This would be
 208 also true for μ_0^M . Thus, $(\mu_f^m + \mu_e^m + \mu_0^m)$ or ψ_t remains unchanged before and after releasing
 209 the swelling pressure.

210 Moreover, undrained unloading would induce negative pore water pressure or capillary
 211 suction ($u_a - u_w$) (Lambe and Whitman, 1969; Nagaraj et al., 1994; Singhal et al., 2015).
 212 Since the effective stress of a soil sample remains during undrained unloading, a decrease in
 213 the net mean stress would be balanced by an equal increase in $(u_a - u_w)$ (Lambe and Whitman,
 214 1969; Nagaraj et al., 1994). Thus, the total potential of the macrostructural pore water after
 215 releasing swelling pressure (μ_M^{un}) would change to the expression shown in Eq. (11).

$$\mu_M^{un} = \mu_0^M - (u_a - u_w)\bar{v}_w = \mu_0^M - P_s\bar{v}_w = -(\psi_a + P_s)\bar{v}_w \quad (11)$$

216 Because of the removal of the swelling pressure, the total potential of the microstruc-
 217 tural pore water (μ_m^{un}) would be reduced to Eq. (12).

$$\mu_m^{\text{un}} = \mu_f^{\text{m}} + \mu_e^{\text{m}} + \mu_0^{\text{m}} = -\psi_t \bar{v}_w \quad (12)$$

218 Comparison of Eq. (11) and Eq. (12) indicates that the total potential of the macrostruc-
 219 tural pore water would be still equal to the total potential of the microstructural pore water
 220 after releasing the swelling pressure. In other words, the thermodynamic equilibrium remains
 221 during undrained unloading, which would mean that there is no water exchange between the
 222 macrostructural pore and the microstructural pore water or that the assumption of undrained
 223 unloading is reasonable. Thus, after releasing the swelling pressure, the total suction of the
 224 saturated bentonite would be equal not only to the capillary suction triggered by swelling pres-
 225 sure release but also to the total suction (ψ_t) of the saturated bentonite under constant volume
 226 condition. Consequently, ($\mu_f^{\text{m}} + \mu_e^{\text{m}} + \mu_0^{\text{m}}$) or ψ_t can be also determined by a chilled-mirror
 227 hygrometer after releasing the swelling pressure.

228 To validate Eq. (9) experimentally, constant volume swelling pressure tests were per-
 229 formed on a Ca-Mg-rich bentonite using various aqueous solutions, i.e. deionized water and
 230 solutions of CaCl_2 . After the swelling pressure tests, the suctions (ψ_a) of the saturating aque-
 231 ous solutions and the total suctions (ψ_t) of the saturated bentonite samples were determined.

232 3. Materials and methods

233 3.1. Materials

234 The bentonite used in this study was Calcigel bentonite from Bavaria, Germany and
 235 purchased from Süd-Chemie AG Moosburg, Germany. The bentonite was composed of mont-
 236 morillonite (60-70%), quartz (6-9%), feldspar (1-4%), kaolinite (1-2%), mica (1-6%), calcite
 237 (2-4%), dolomite (1-3%) and other minerals (3%). The total specific surface area of the ben-
 238 tonite was measured by the ethylene glycol monoethyl ether (EGME) method (Cerato and

239 Lutenegger, 2002) and was found to be $436 \text{ m}^2/\text{g}$. The total cation exchange capacity (CEC)
 240 of the bentonite was $74 \text{ cmol}(+)/\text{kg}$. More than 85% of the exchangeable cations in the ben-
 241 tonite were divalent calcium and magnesium ions and about 12% of the exchangeable cations
 242 were monovalent sodium ions (Schanz and Tripathy, 2009; Baille et al., 2010). Based on the
 243 measurements of osmotic suction using the squeezing technique (Fredlund et al., 2012), Arifin
 244 and Schanz (2009) noted that the osmotic suction of Calcigel bentonite remained at about 0.05
 245 MPa for a large range of water content. This indicated that Calcigel contains some soluble
 246 ions that contribute to about 0.05 MPa osmotic suction. The liquid limit, plastic limit and
 247 particle specific gravity of the bentonite were 119%, 45% and 2.80, respectively.

248 **3.2. Experimental methods**

249 **3.2.1. Sample preparation**

250 Bentonite-water mixtures were prepared at target water contents of 9% and 20% by
 251 adding the required amounts of deionized water to the bentonite. After mixing bentonite and
 252 water, the bentonite-water mixtures were kept in a two-layer plastic bag for about two weeks
 253 for moisture equilibration. The water contents of the mixtures were determined by oven
 254 drying method at a temperature of 105°C prior to preparing samples for swelling pressure
 255 tests. The total suctions of the mixtures were determined by using AquaLab-3TE chilled-
 256 mirror hygrometer (Decagon Devices, 1999-2009; Leong et al., 2003) and Kelvin's law (i.e.
 257 Eq. (8)). The accuracy of the device in terms of the relative humidity was $\pm 0.3\%$. If the
 258 total suction of a soil sample was equal to 0.3 MPa, the determined total suction could vary
 259 from 0 to 0.8 MPa at 22°C due to the accuracy of $\pm 0.3\%$. If the total suction of a soil sample
 260 was equal to 3.0 MPa, the determined total suction could vary from 2.6 to 3.4 MPa at 22°C .
 261 This indicates that the accuracy of $\pm 0.3\%$ could cause a significant total suction measurement
 262 error (i.e. up to $\pm 140\%$) if the total suction of a soil sample was less than 0.3 MPa.

263 Compacted bentonite samples, 50 mm in diameter and 15 ± 0.02 mm in height, were

264 prepared by statically compacting bentonite-water mixtures inside the oedometer ring by using
265 a 15-tonne capacity compression testing machine. The samples were compacted by applying
266 uniaxial loads. The initial compaction conditions of the as-compacted samples and aqueous
267 solutions used to saturate the samples during the swelling pressure tests are shown in Table
268 1.

269 **3.2.2. Determination of swelling pressure, water content and total suction**

270 An isochoric swelling pressure device (Fig. 1) (Romero, 1999; Schanz and Tripathy,
271 2009) was used in this study for measuring the swelling pressures of compacted bentonite
272 samples. After the static compaction process, the as-compacted sample inside the sample
273 ring was placed in the swelling pressure device. Samples CB-0 to CB-6 with compaction dry
274 densities varying between 1.20 to 1.83 Mg/m³ (Table 1) were hydrated by supplying deionized
275 water. Samples CB-2, CB-3 and CB-4 had very similar compaction conditions (dry density
276 = 1.57 Mg/m³ and water content = 20%). Samples CB-7, CB-8, CB-9, and CB-10 (dry
277 density = 1.59 Mg/m³) were hydrated with deionized water, 0.5, 1.0 and 2.0M CaCl₂ solutions,
278 respectively. The hydrating fluids were supplied from burettes attached to the bottom fluid
279 reservoirs of the devices. During the swelling pressure tests, the CaCl₂ solutions were renewed
280 periodically for maintaining the constant concentration of the solutions.

281 The swelling pressures tests for all samples were terminated once the swelling pressure
282 was found to be constant. Samples CB-0 and CB-4 were dismantled after about 17 and
283 19 days, respectively. For the other samples the testing duration well exceeded 30 days.
284 Following termination of a test, the fluid supply to the sample was stopped. Subsequently,
285 samples of the aqueous solution (i.e. the hydrating fluid) were collected (in duplicate) from
286 the bottom fluid reservoir for determining the suctions of the fluid. Before dismantling the
287 device, pressurized humid air (relative humidity = 100%) generated by deionized water was
288 used to flush the bottom and top fluid reservoirs to minimize fluid uptake by samples upon

unloading. Afterwards, the sample was removed from the isochoric device for determining total suction (ψ_t) and water content.

In order to explore the homogeneity of samples in terms of the water content and suction, the bentonite samples were cut into three parts that represent the top, middle and bottom layers, respectively. The water contents and total suctions of the representative samples were determined by the oven drying method (105°C) and the chilled-mirror hygrometer, respectively. Sufficient care was exercised to minimize the evaporation water from the samples during preparing samples for water content and suction measurements.

3.2.3. Determination of suctions of hydrating fluids/aqueous solutions

The suction of the deionized water (kPa) used in this study was determined from the electrical conductivity (EC) measurements (mS/cm) using Eq. (13) (Rao and Shivananda, 2005).

$$\psi_a = 38.54EC^{1.0489}. \quad (13)$$

The electrical conductivity (EC) of the deionized water used in this study was found to be about 0.03 mS/cm. Thus, the calculated suction of the deionized water used was approximately 0.001 MPa and was nearly equivalent to the suction of a 0.0001 M CaCl_2 solution based on van't Hoff equation. The suctions of CaCl_2 solutions after the swelling pressure tests were determined by using the chilled-mirror hygrometer and Kelvin's law. The suctions of 0.5 M, 1 M and 2 M CaCl_2 solutions were found to be 3.03, 8.42, and 20.55 MPa, respectively. These values were found to be similar to the suctions of the solutions prior to the swelling pressure tests and remained within the measurement accuracy of the chilled-mirror hygrometer.

4. Results and discussion

4.1. Swelling pressure

The elapsed time versus swelling pressure for bentonite samples CB-0 to CB-7 is shown in Fig. 2a. Similarly, Fig. 2b presents the evolution of swelling pressures in case of samples CB-7, CB-8, CB-9, and CB-10 that were hydrated with deionized water, 0.5, 1.0 and 2.0 M CaCl_2 solutions, respectively. Swelling pressure equilibrium time was defined as the time when the variation of swelling pressure started to be less than 5 kPa per day. The swelling pressure equilibrium time was found to increase with an increase in the sample dry density (Fig. 2a). The equilibrium time for sample CB-0 (dry density = 1.2 Mg/m^3) was about 60 h, whereas it was found to be about 440 h for sample CB-6 with a compaction dry density of 1.83 Mg/m^3 . For a given dry density of 1.59 Mg/m^3 , the type of hydrating fluid (i.e., water or CaCl_2 solutions) had no significant influence on the equilibrium time. In this case, the swelling pressure equilibrated in about 270 h.

An increase in the swelling pressure equilibrium time with an increase in the dry density is attributed to an increase in the static compaction pressure which in turn affects the pore-size distribution and permeability of compacted bentonites (Pusch, 1980a; Lloret et al., 2003). Studies on the pore size distribution of the compacted clays have shown dual-structure pore size distributions with intra-aggregate and inter-aggregate pores (Sridharan et al., 1971; Pusch and Yong, 2006; Delage et al., 2006). As the dry density increases, the inter-aggregate pore size decreases, whereas the intra-aggregate pore size may remain almost constant (Lloret et al., 2003; Romero and Simms, 2008; Li and Zhang, 2009; Wang et al., 2013; Seiphoori et al., 2014). The flow of liquid water in compacted bentonites initially occurs within the inter-aggregate pores and then in the intra-aggregate pores. Since the permeability of the compacted bentonites is mainly governed by the inter-aggregate pores, a reduction in the size of the inter-aggregate pores either due to an increase in compaction dry density or due to

334 swelling decelerates the development of swelling pressure.

335 The effect of sample dry density on the equilibrium swelling pressure is presented in
336 Figs. 3. The magnitude of swelling pressure at equilibrium was found to be influenced by the
337 sample dry density. As can be seen from Fig 3, with deionized water as the hydrating fluid
338 the swelling pressure increased from 0.3 to 10.5 MPa with an increase in the dry density from
339 1.20 to 1.83 Mg/m³. The differences in the swelling pressures of samples CB-2, CB-3, and
340 CB-4 (dry density = 1.57 Mg/m³) remained less than about 0.5 MPa. Based on the diffuse
341 double layer theory as applicable to interacting clay platelet systems, a dry density of 1.55
342 Mg/m³ for Calcigel bentonite delimits the osmotic swelling (Schanz and Tripathy, 2009). If
343 the dry density is less than the threshold dry density, diffuse double layer repulsion governs the
344 swelling pressure. An increase in the dry density decreases the distance between clay platelets,
345 increases the ion concentration difference between the central plane between clay platelets
346 and bulk solution and further increases the swelling pressure (Bolt, 1956; Van Olphen, 1977;
347 Schanz and Tripathy, 2009). If dry density is greater than the threshold dry density, hydration
348 forces control the swelling pressure. An increase in dry density decreases the space between
349 interlayers, increases hydration forces and further increases the swelling pressure (Van Olphen,
350 1977; Schanz and Tripathy, 2009).

351 In the case of samples with a constant dry density of 1.59 Mg/m³, the equilibrium
352 swelling pressure decreased with an increase in CaCl₂ concentration (Fig. 2b). A reduction in
353 the swelling pressure from 2.98 to 2.10 MPa was found to occur (i.e. a decrease of about 30%)
354 when the concentration of CaCl₂ was increased from 0.0001 to 2.0 M. Similar experimental
355 results concerning the influence of salt solution concentration on the swelling pressure have
356 been reported by several researchers (Pusch, 1980*b*; Bucher and Max, 1989; Pusch et al., 1990;
357 Karnland et al., 2005; Villar and Lloret, 2008*a*; Castellanos et al., 2008; Zhu et al., 2013;
358 Tripathy et al., 2014*b*).

4.2. Water content and total suction profiles

Figure 4 presents the profiles of the water content and the total suction for samples CB-0 to CB-6 that were saturated with deionized water. Figure 5 presents the profiles of the water content and the total suction for samples CB-7 to CB-10 that were saturated with CaCl_2 solutions. Due to the water uptake by the samples during the swelling pressure tests, the water contents of the samples at the end of the swelling pressure tests were found to be higher than the initial water contents (Figs. 4a and 5a). For any sample, the final water content was nearly the same along the depth of the sample. The degree of saturation of all the samples tested was determined based on the final water contents, the dimensions of the samples and the volume-mass relationships. The degree of saturation of all samples indicated that all samples were fully saturated at the end of the swelling pressure tests.

As compared to the initial total suctions, the total suctions of all samples at the end of the swelling pressure tests were found to have decreased (Figs. 4b and 5b). The total suction profiles in most cases were found to be uniform. A variation of the total suction along the depth of sample CB-4 was noted, in which case the total suction towards the top of the sample was found to be greater than that occurred towards the bottom (Fig. 4b). The variation of the total suction along the depth of sample CB-4 is attributed to a shorter testing time (19 days) than for samples CB-2 and CB-3 that had similar compaction conditions, but were tested for longer durations (more than 32 days).

The effect of dry density on the final water content and total suction of the samples tested with deionized water is shown in Fig. 6a. The average values of the final water contents and total suctions are plotted in Fig. 6a. With an increase in the dry density, the final water content decreased and the total suction was found to increase.

The amount of water present in the saturated bentonite affects the total suction and thus the magnitude of the total suction depends on the dry density of the saturated bentonite.

At high dry densities, the capillary effect disappears and the diffuse double layer is suppressed, but the short-range adsorption effects (surface and ion hydration within the interlayers) remain (Yong, 1999; Schanz and Tripathy, 2009). In this case, the matric suction caused by the short-range adsorption effects contributes to the total suction and its magnitude increases with a decrease in the thickness of the water layer within the interlayers. At low dry densities, the matric suction due to the short-range adsorption effects diminishes, whereas the one due to the diffuse double layer forces remains. In this case, the matric suction caused by diffuse double layer forces contributes to the total suction and its magnitude increases with a decrease in the thickness of the water layer within clay platelets (Yong, 1999; Tripathy et al., 2014a).

The concentration of CaCl_2 in the hydrating fluids affected the total suctions of samples CB-7 to CB-10 (Fig. 6b). Since the samples had the same dry density, the saturated water contents remained similar regardless of the concentration of the hydrating fluids. However, the total suction increased significantly with an increase in the CaCl_2 concentration. With an increase in the CaCl_2 concentration from 0.0001 to 2.0 M, the total suction increased from 3.2 to 22.7 MPa. The increase in the total suction with the CaCl_2 concentration is attributed primarily to an increase in osmotic suction caused by an increase in the amount of dissolved salts (CaCl_2) in the macrostructural pore fluid (Rao and Thyagaraj, 2007; Musso et al., 2013).

4.3. Total suction and swelling pressure

The experimental results presented in Figs. 3 and 6 show that both swelling pressure and total soil suction were dependent on the dry density of the bentonite and salt concentration of the hydrating fluids. Total suction versus swelling pressure plot is shown in Fig. 7. For the bentonite samples that were hydrated with deionized water (samples CB-0 to CB-7), with the exception of sample CB-0, the total suction was nearly equal to the swelling pressure. For sample CB-0, the total suction (0.8 MPa) was greater than the swelling pressure (0.3 MPa), which was probably the result of a significant total suction measurement error. As mentioned

in the section of Materials and methods, the total suction measurement error was up to $\pm 140\%$ if the total suction of a soil was less than 0.3 MPa. This significant error (i.e. $\pm 140\%$) could have overestimated the real total suction of sample CB-0. In the case of the samples that were hydrated with CaCl_2 solutions (samples CB-8 to CB-10), the total suction was considerably greater than the corresponding swelling pressure. The test results showed that if the hydrating fluid was water ($\psi_a = 0.001$ MPa), there was a good agreement between swelling pressure and total suction. Disagreement between total suction and swelling pressure was only observed for the samples that were hydrated with solutions having high salt concentration.

4.4. Suction of hydrating fluids and total suction

Figure 8 presents the suctions of the aqueous solutions used for hydrating the bentonite samples versus the total suctions of all samples. As can be expected, the total suctions of the samples that were saturated with deionized water (samples CB-0 to CB-7) far exceeded the suction of water ($\psi_a = 0.001$ MPa). The total suction of the bentonite saturated with deionized water increased from 0.8 MPa to 12.8 MPa with an increase in the dry density from 1.2 to 1.83 Mg/m^3 (Fig. 6a). For samples CB-8 to CB-10 that were saturated with CaCl_2 solutions, the total suctions were found to be greater than the suctions of aqueous solutions, too. For the bentonite saturated with CaCl_2 solutions, the total suction increased from 5.4 to 22.7 MPa with an increase in the suction of CaCl_2 solutions from 3.0 to 20.6 MPa.

4.5. Swelling pressure and difference between total suction and suction of hydrating fluids

The swelling pressures (P_s) of saturated bentonites are plotted against the differences between the total suctions of saturated bentonites and the suctions of the hydrating fluids ($\psi_t - \psi_a$) in Fig. 9. In addition to the test results obtained from this study on the Ca-Mg-rich bentonite, the test results reported by Karnland et al. (2005) on a Na-bentonite are

also shown in Fig. 9 for the tests with water and various NaCl solutions. In their study, the compacted Na bentonite samples under constant volume condition were saturated with solutions of concentration from 0.0001 to 3 M NaCl. After the swelling pressures reached equilibrium, the samples were extracted from the constant volume device for total suction measurement. Details for the material and experimental methods and results could be found in their publication. Because the suctions of the various concentrations of NaCl were not measured in their study, these suctions were determined based on a method proposed by Lang (1976).

With the exception of sample CB-0, the difference between the total suction of a saturated sample and the suction of the hydrating fluid used to saturate the sample was nearly equal to the swelling pressure of the saturated sample for both bentonites. The results presented in Fig. 9 validate Eq. (9) that was derived based on the thermodynamics of soil moisture. For sample CB-0, the difference in its total suction and the suction of deionized water used to saturate the sample was found to be greater than its swelling pressure. As explained above, the significant total suction measurement error (i.e. $\pm 140\%$) could have overestimated the real total suction of sample CB-0. The results in Fig. 9 show that there is a strong linkage between the swelling pressure of saturated bentonites, the total suction of saturated bentonites and the suction of hydrating fluid. Measurements of any two parameters would be sufficient to assess the unknown parameter. The linkage between these three parameters indicates that the total suction of a bentonite caused by the adsorptive and osmotic forces would not dissipate when the bentonite is saturated with aqueous solutions under constant volume condition.

5. Conclusions

The linkage between the swelling pressure of saturated bentonites, the total suction of saturated bentonites and the suction of the aqueous solutions used to saturate bentonites was

458 examined based on the thermodynamics of soil moisture. To validate the derived equation,
459 constant volume swelling pressure tests and suction measurements were carried out on the Ca-
460 Mg-rich bentonite in the laboratory. The following conclusions were drawn from the study.

461 1. The time taken for the swelling pressure to reach an equilibrium increased with
462 the increase in the dry density of the bentonite, which was attributed to a decrease in the
463 permeability of the bentonite at high compaction dry densities.

464 2. In addition to the swelling pressure of the saturated bentonite, the total suction
465 of the saturated bentonite was significantly affected by the compaction dry density of the
466 bentonite and the salt concentration of the hydrating fluids, too. The increase in the total
467 suction of the saturated bentonite with the compaction dry density results from the decrease
468 the amount of water present in the saturated bentonite. The increase in the total suction of the
469 saturated bentonite with the salt concentration of the hydrating fluids is attributed primarily
470 to an increase in the osmotic suction caused by an increase in the amount of dissolved salts
471 in the macrostructural pore fluids.

472 3. The total suction of the saturated bentonite was nearly equal to the swelling pressure
473 in case of water as the hydrating fluid. However, the total suction was significantly greater
474 than the swelling pressure in case of CaCl_2 solutions as the hydrating fluid. Moreover, the total
475 suction of the saturated bentonite was found to be greater than the suction of the hydrating
476 fluids.

477 4. Based on the experimental results from this study and those reported in the literature
478 it was found that the difference between the total suction of saturated bentonites and the
479 suction of the aqueous solutions used to saturate the bentonites is approximately equal to
480 the swelling pressure of saturated bentonites. The linkage between these three parameters
481 indicates that the total suction of a bentonite caused by the adsorptive and osmotic forces
482 would not dissipate when the bentonite is saturated with aqueous solutions under constant
483 volume condition. The present finding extends the relationship suggested by Croney (1952);

Kassiff and Shalom (1971); Townr (1981); Karnland et al. (2005). Moreover, the linkage between these three parameters provides the framework for establishing a quantitative linkage between swelling pressure of bentonites and hydro-mechanical-chemical boundary conditions in the deep geological repositories.

6. Acknowledgements

The financial support provided by the Deutsche Forschungsgemeinschaft (DFG) through research grant no. SCHA 675/16-1 is gratefully acknowledged. The first author is grateful to the Chinese Scholarship Council and Ruhr University Research School PLUS (Germany's Excellence Initiative [DFG GSC 98/3]) for their financial assistance. The second author acknowledges the Visiting International Professor grant received from Research School PLUS, Ruhr University Bochum, Germany. The authors also thank the unknown reviewers and associate Editor Dr Villar for their suggestions to improve the manuscript.

7. Reference

- Agus, S., Arifin, Y., Tripathy, S. and Schanz, T. (2013), 'Swelling pressure-suction relationship of heavily compacted bentonite-sand mixtures', *Acta Geotech.* **8**(2), 155–165.
- Alonso, E. E., Gens, A. and Josa, A. (1990), 'A constitutive model for partially saturated soils', *Géotechnique*. **40**(3), 405–430.
- Arifin, Y. F. (2008), Thermo-hydro-mechanical behavior of compacted bentonite-sand mixtures: an experimental study, PhD thesis, Bauhaus-University Weimar.
- Arifin, Y. F. and Schanz, T. (2009), 'Osmotic suction of highly plastic clays', *Acta Geotech.* **4**(3).
- Baille, W., Tripathy, S. and Schanz, T. (2010), 'Swelling pressures and one-dimensional compressibility behaviour of bentonite at large pressures', *Appl. Clay Sci.* **48**(3), 324 – 333.

506 Bergaya, F., Theng, B. and Lagaly, G., eds (2006), *Handbook of clay science. In: Developments in*
507 *Clay Science*, Vol. 1, Elsevier, Amsterdam.

508 Bolt, G. (1956), ‘Physico-chemical analysis of the compressibility of pure clays’, *Géotechnique*.
509 **6**(2), 86–93.

510 Bolt, G. and Miller, R. (1958), ‘Calculation of total and component potentials of water in soil’, *Eos*.
511 **39**(5), 917–928.

512 Bucher, F. and Max, M. (1989), ‘Bentonite as a containment barrier for the disposal of highly
513 radioactive wastes’, *Appl. Clay Sci.* **4**(2), 157–177.

514 Castellanos, E., Villar, M., Romero, E., Lloret, A. and Gens, A. (2008), ‘Chemical impact on the
515 hydro-mechanical behaviour of high-density FEBEX bentonite’, *Phys. Chem. Earth.* **33**, S516–
516 S526.

517 Cerato, A. and Lutenecker, A. (2002), ‘Determination of surface area of fine-grained soils by the
518 ethylene glycol monoethyl ether (EGME) method’, *Geotech. Test. J.* **25**, 315–321.

519 Cronley, D. (1952), ‘The movement and distribution of water in soils’, *Géotechnique*. **3**(1), 1–16.

520 Cui, Y.-J., Tang, A. M., Loiseau, C. and Delage, P. (2008), ‘Determining the unsaturated hydraulic
521 conductivity of a compacted sand–bentonite mixture under constant-volume and free-swell condi-
522 tions’, *Phys. Chem. Earth.* **33**, S462–S471.

523 Decagon Devices, I. (1999-2009), *Water Activity Meter Operator’s Manual for Aqualab Series 3*,
524 Decagon Devices, Inc.

525 Delage, P., Marcial, D., Cui, Y. J. and Ruiz, X. (2006), ‘Ageing effects in a compacted bentonite: a
526 microstructure approach’, *Géotechnique*. **56**(5), 291–304.

527 Edlefsen, N. E. and Anderson, A. B. (1943), *Thermodynamics of soil moisture*, University of Cali-
528 fornia.

- 529 Fredlund, D. G., Rahardjo, H. and Fredlund, M. D. (2012), *Unsaturated soil mechanics in engineering*
530 *practice*, John Wiley & Sons, Inc.
- 531 Gens, A. and Alonso, E. E. (1992), ‘A framework for the behaviour of unsaturated expansive clays’,
532 *Can. Geotech. J.* **29**(6), 1013–1032.
- 533 Iwata, S., Tabuchi, T., Warkentin, B. P. et al. (1995), *Soil-water interactions: mechanisms and*
534 *applications*, number Ed. 2, Marcel Dekker, Inc.
- 535 Karnland, O., Muurinen, A. and Karlsson, F. (2005), Bentonite swelling pressure in nacl solutions-
536 experimentally determined data and model calculations, in A. L. Eduardo E. Alonso, ed., ‘Ad-
537 vances in Understanding Engineering Clay Barriers’, pp. 241–256.
- 538 Kassiff, G. and Shalom, A. B. (1971), ‘Experimental relationship between swell pressure and suction’,
539 *Géotechnique*. **21**(3), 245–255.
- 540 Komine, H. and Ogata, N. (1996), ‘Prediction for swelling characteristics of compacted bentonite’,
541 *Can. Geotech. J.* **33**(1), 11–22.
- 542 Lambe, T. W. and Whitman, R. V. (1969), *Soil mechanics*, John Wiley & Sons.
- 543 Lang, A. (1976), ‘Osmotic coefficients and water potentials of sodium chloride solutions from 0 to
544 40°C’, *Aust. J. Chem.* **20**(9), 2017–2023.
- 545 Leong, E.-C., Tripathy, S. and Rahardjo, H. (2003), ‘Total suction measurement of unsaturated soils
546 with a device using the chilled-mirror dew-point technique’, *Géotechnique*. **53**(2), 173–182.
- 547 Li, X. and Zhang, L. (2009), ‘Characterization of dual-structure pore-size distribution of soil’, *Can.*
548 *Geotech. J.* **46**(2), 129–141.
- 549 Lloret, A., Villar, M. V., Sanchez, M., Gens, A., Pintado, X. and Alonso, E. E. (2003), ‘Mechanical
550 behaviour of heavily compacted bentonite under high suction changes’, *Géotechnique*. **53**(1), 27–40.
- 551 Low, P. and Deming, J. M. (1953), ‘Movement and equilibrium of water in heterogeneous systems
552 with special reference to soils’, *Soil Sci.* **75**(3), 187–202.

- 553 Low, P. F. (1987), ‘Structural component of the swelling pressure of clays’, *Langmuir* **3**(1), 18–25.
- 554 Low, P. F. and Anderson, D. M. (1958), ‘Osmotic pressure equations for determining thermodynamic
555 properties of soil water’, *Soil Sci.* **86**(5), 251–253.
- 556 Lu, N. and Likos, W. J. (2004), *Unsaturated soil mechanics*, Wiley.
- 557 Manca, D., Ferrari, A. and Laloui, L. (2015), ‘Fabric evolution and the related swelling behaviour of
558 a sand/bentonite mixture upon hydro-chemo-mechanical loadings’, *Géotechnique* **66**(1), 41–57.
- 559 Măsin, D. and Khalili, N. (2016), ‘Swelling phenomena and effective stress in compacted expansive
560 clays’, *Can. Geotech. J.* **53**(1), 134–147.
- 561 Mitchell, J. (1962), Components of pore water pressure and their engineering significance, in E. IN-
562 GERSON, ed., ‘Clays Clay Miner.’, Pergamon, pp. 162–184.
- 563 Mokni, N. and Barnichon, J.-D. (2016), ‘Hydro-mechanical analysis of SEALEX in-situ tests-Impact
564 of technological gaps on long term performance of repository seals’, *Eng. Geol.* **205**, 81–92.
- 565 Musso, G., Romero, E. and Vecchia, G. (2013), ‘Double-structure effects on the chemo-hydro-
566 mechanical behaviour of a compacted active clay’, *Géotechnique* **63**(3), 206–220.
- 567 Nagaraj, T. S., Murthy, B. R. S. and Vatsala, A., eds (1994), *Analysis and Prediction of Soil Be-
568 haviour*, New Age International (P) Ltd., New Delhi.
- 569 Navarro, V., De la Morena, G., González-Arteaga, J., Yustres, Á. and Asensio, L. (2018), ‘A mi-
570 crostructural effective stress definition for compacted active clays’, *Geomech. Energy Environ.*
571 **15**, 47–53.
- 572 Navarro, V., De la Morena, G., Yustres, Á., González-Arteaga, J. and Asensio, L. (2017a), ‘Predicting
573 the swelling pressure of mx-80 bentonite’, *Appl. Clay Sci.* **149**, 51–58.
- 574 Pusch, R. (1980a), Permeability of highly compacted bentonite, Technical report, Swedish Nuclear
575 Fuel and Waste Management Co.

576 Pusch, R. (1980*b*), Swelling pressure of highly compacted bentonite, Technical report, Swedish Nu-
577 clear Fuel and Waste Management Co.

578 Pusch, R., Karnland, O. and Hokmark, H. (1990), GMM-a general microstructural model for qualita-
579 tive and quantitative studies of smectite clays, Technical report, Swedish Nuclear Fuel and Waste
580 Management Co.

581 Pusch, R. and Yong, R. N. (2006), *Microstructure of smectite clays and engineering performance*,
582 CRC Press.

583 Rao, S. M. and Shivananda, P. (2005), ‘Role of osmotic suction in swelling of salt-amended clays’,
584 *Can. Geotech. J.* **42**(1), 307–315.

585 Rao, S. M. and Thyagaraj, T. (2007), ‘Swell-compression behaviour of compacted clays under chem-
586 ical gradients’, *Can. Geotech. J.* **44**(5), 520–532.

587 Romero, E. (1999), Characterisation and thermo-hydro-mechanical behaviour of unsaturated boom
588 clay: an experimental study, PhD thesis, Technical University of Catalonia.

589 Romero, E. and Simms, P. H. (2008), ‘Microstructure investigation in unsaturated soils: a review with
590 special attention to contribution of mercury intrusion porosimetry and environmental scanning
591 electron microscopy’, *Geotech. Geol. Eng.* **26**(6), 705–727.

592 Schanz, T. and Tripathy, S. (2009), ‘Swelling pressure of a divalent-rich bentonite: Diffuse double-
593 layer theory revisited’, *Water Resour. Res.* **45**(5), W00C12.

594 Seiphoori, A., Ferrari, A. and Laloui, L. (2014), ‘Water retention behaviour and microstructural
595 evolution of mx-80 bentonite during wetting and drying cycles’, *Géotechnique*. **64**(9), 721–734.

596 Singhal, S., Houston, S. L. and Houston, W. (2015), ‘Swell pressure, matric suction, and matric
597 suction equivalent for undisturbed expansive clays’, *Can. Geotech. J.* **52**(3), 356–366.

598 Sridharan, A., Altschaeffl, A. and Diamond, S. (1971), ‘Pore size distribution studies’, *J.Soi. Mech.*
599 *Found. Div.* **97**(5), 771–787.

600 Townenr, G. D. (1981), ‘The correction of in situ tensiometer readings for overburden pressures in
601 swelling soils’, *J. Soil Sci.* **32**(4), 499–504.

602 Tripathy, S., Bag, R. and Thomas, H. R. (2014b), ‘Effects of post-compaction residual lateral stress
603 and electrolyte concentration on swelling pressures of a compacted bentonite’, *Geotech. Geol. Eng.*
604 **32**(4), 749–763.

605 Tripathy, S., Tadza, M. Y. M. and Thomas, H. R. (2014a), ‘Soil-water characteristic curves of clays’,
606 *Can. Geotech. J.* **51**(8), 869–883.

607 Van Olphen, H. (1977), *An introduction to clay colloid chemistry: for clay technologists, geologists,*
608 *and soil scientists*, 2 edn, Wiley, New York.

609 Viani, B. E., Low, P. F. and Roth, C. B. (1983), ‘Direct measurement of the relation between
610 interlayer force and interlayer distance in the swelling of montmorillonite’, *Journal of Colloid and*
611 *Interface Science* **96**(1), 229 – 244.

612 Villar, M. and Lloret, A. (2008a), ‘Influence of dry density and water content on the swelling of a
613 compacted bentonite’, *Appl. Clay Sci.* **39**(1-2), 38–49.

614 Villar, M. V. and Lloret, A. (2008b), ‘Influence of dry density and water content on the swelling of
615 a compacted bentonite’, *Appl. Clay Sci.* **39**(1), 38–49.

616 Villar, M. V., Martín, P. L., Romero, F. J., Iglesias, R. J. and Gutiérrez-Rodrigo, V. (2016), ‘Saturation of barrier materials under thermal gradient’, *Geomech. Energy Environ.* **8**, 38–51.

617

618 Wang, Q., Tang, A. M., Cui, Y.-J., Delage, P., Barnichon, J.-D. and Ye, W.-M. (2013), ‘The effects
619 of technological voids on the hydro-mechanical behaviour of compacted bentonite-sand mixture’,
620 *Soils Found.* **53**(2), 232–245.

621 Wang, Q., Tang, A. M., Cui, Y.-J., Delage, P. and Gatmiri, B. (2012), ‘Experimental study on the
622 swelling behaviour of bentonite/claystone mixture’, *Engineering Geology* **124**(Supplement C), 59
623 – 66.

- 624 Ye, W.-M., Cui, Y.-J., Qian, L.-X. and Chen, B. (2009), ‘An experimental study of the water transfer
625 through confined compacted gmz bentonite’, *Eng. Geol.* **108**(3), 169–176.
- 626 Yigzaw, Z., Cuisinier, O., Massat, L. and Masrouri, F. (2016), ‘Role of different suction components
627 on swelling behavior of compacted bentonites’, *Appl. Clay Sci.* **120**, 81–90.
- 628 Yong, R. (1999), ‘Soil suction and soil-water potentials in swelling clays in engineered clay barriers’,
629 *Eng. Geol.* **54**(1), 3–13.
- 630 Yong, R. N. and Warkentin, B. P. (1975), *Soil Properties and Behaviour. In: Developments in*
631 *Geotechnical Engineering*, Vol. 5, Elsevier, Amsterdam.
- 632 Zhu, C.-M., Ye, W.-M., Chen, Y.-G., Chen, B. and Cui, Y.-J. (2013), ‘Influence of salt solutions
633 on the swelling pressure and hydraulic conductivity of compacted GMZ01 bentonite’, *Eng. Geol.*
634 **166**, 74–80.

- Time for swelling pressure to reach equilibrium increases with bentonite density.
- Bentonite density and concentration of solutions affect the suction of bentonites.
- Swelling pressure equals the difference in suction between bentonite and solutions.

Table 1. Initial compaction conditions of bentonite samples and the types of aqueous solution used for saturating the samples during the swelling pressure tests

Sample no.	Initial compaction conditions				Aqueous solutions
	Dry density	Water content	Degree of saturation	Total soil suction★	
	(Mg/m ³)	(%)	(%)	(MPa)	
CB-0	1.20	20.0	42.0	13.7	Deionized water
CB-1	1.41	20.0	56.2	13.7	Deionized water
CB-2	1.57	20.0	71.6	13.7	Deionized water
CB-3	1.57	20.0	71.8	13.7	Deionized water
CB-4	1.58	20.0	72.6	13.7	Deionized water
CB-5	1.66	20.0	81.6	13.7	Deionized water
CB-6	1.83	16.4 ^α	86.2	52.4	Deionized water
CB-7	1.59	9.0	33.3	166.3	Deionized water
CB-8	1.59	9.0	33.2	166.3	0.5 M CaCl ₂
CB-9	1.59	9.0	33.3	166.3	1.0 M CaCl ₂
CB-10	1.59	9.0	33.3	166.3	2.0 M CaCl ₂

*, the targeted water content of 20% could not achieved due to experimental error; ★, determined using chilled-mirror hygrometer and Kelvin’s law.

Fig. 1. Schematics of swelling pressure measurement using constant volume test set-up and of structure of compacted bentonite sample

Fig. 2. Elapsed time versus swelling pressure for the samples (a) saturated with deionized water and (b) saturated with CaCl_2 solutions of different concentrations

Fig. 3. Effect of initial dry density on swelling pressure

Fig. 4. Profiles of (a) water content and (b) total suction for the swelling pressure tests with deionized water (water contents of samples CB-2 and CB-4 correspond to mean water contents)

Fig. 5. Profiles of (a) water content and (b) total suction for the swelling pressure tests with CaCl_2 solutions

Fig. 6. Effects of (a) initial dry density and (b) CaCl₂ concentration on the water content and total suction of the saturated bentonite samples after swelling pressure tests

Fig. 7. Total suction versus swelling pressure plot for saturated bentonite samples at the end of swelling pressure tests

Fig. 8. Suction of hydrating fluid versus total suction of the saturated samples at the end of the swelling pressure tests

Fig. 9. Difference between the total suction of saturated bentonites and the suction of hydrating fluid versus the swelling pressure of saturated bentonites for tests with deionized water and various salt solutions (0 M in the legend corresponds to deionized water)

Linkage between swelling pressure, total suction of saturated bentonites and suction of saturating aqueous solutions

Abstract: In deep geological repositories, compacted bentonites have been proposed for use as barrier materials for isolating nuclear waste. The prevailing hydro-mechanical-chemical boundary conditions in the repositories can affect the swelling capacity of compacted bentonites. The present study examines the linkage between the swelling pressure of saturated bentonites, the total suction of saturated bentonites and the suction of hydrating fluids. An equation describing the linkage between these parameters was derived based on the thermodynamics of soil moisture. To validate the derived relationship, laboratory tests involving constant volume swelling pressure tests and total suction measurements after the swelling pressure tests were carried out on a selected Ca-Mg-rich bentonite. Seven bentonite samples with compaction dry density ranging from 1.20 and 1.83 Mg/m³ were hydrated with deionized water, whereas four samples with a dry density of 1.59 Mg/m³ were hydrated with 0.0001 to 2.0 M CaCl₂ solutions. The total suctions of the saturated bentonite and the hydrating fluids were determined by using a chilled-mirror hygrometer. The total suction of the saturated bentonite was found to be affected by the compaction dry density and the suction of the hydrating fluids. The experimental results from the present study and from the literature demonstrated that the total suction of saturated bentonites minus the suction of the hydrating fluid used to saturate bentonites is approximately equal to the swelling pressure of saturated bentonites.

Key words: Expansive soils; bentonite; swelling pressure; suction; thermodynamics of soil moisture; radioactive waste disposal

LaTeX Source Files

[Click here to download LaTeX Source Files: latex.zip](#)