

This is an Open Access document downloaded from ORCA, Cardiff University's institutional repository: <https://orca.cardiff.ac.uk/id/eprint/111690/>

This is the author's version of a work that was submitted to / accepted for publication.

Citation for final published version:

Rucinska, Emilia, Miedziak, Peter, Pattisson, Samuel, Brett, Gemma, Iqbal, Sarwat, Morgan, David John , Sankar, Meenakshisundaram and Hutchings, Graham 2018. Cinnamyl alcohol oxidation using supported bimetallic Au-Pd nanoparticles: an investigation of autoxidation and catalysis. *Catalysis Science and Technology* 8 (11) , pp. 2987-2997. 10.1039/C8CY00155C

Publishers page: <http://dx.doi.org/10.1039/C8CY00155C>

Please note:

Changes made as a result of publishing processes such as copy-editing, formatting and page numbers may not be reflected in this version. For the definitive version of this publication, please refer to the published source. You are advised to consult the publisher's version if you wish to cite this paper.


This version is being made available in accordance with publisher policies. See <http://orca.cf.ac.uk/policies.html> for usage policies. Copyright and moral rights for publications made available in ORCA are retained by the copyright holders.




## Electronic Supplementary Information (ESI)

### Cinnamyl alcohol oxidation using supported bimetallic Au-Pd nanoparticles: an investigation of autoxidation and catalysis

Emilia Rucinska, Peter J. Miedziak, Samuel Pattisson, Gemma L. Brett, Sarwat Iqbal, David J. Morgan, Meenakshisundaram Sankar and Graham, J. Hutchings.\*



**ESI Figure 1** Oxidation of cinnamyl alcohol under different oxygen pressure carried out in the presence and absence of the catalyst as a function of reaction time. Reaction conditions: 1%AuPd/TiO<sub>2</sub>(Imp), 10 mg; oxygen pressure, 1-3 bar; temperature, 120 °C; 0.5 M cinnamyl alcohol in toluene. **Full figures-** reactions carried out in the absence of a catalyst: 1 bar (■); 2 bar (◆), 3 bar (▲); **empty figure-** reactions carried out in the presence of a catalyst: 1 bar (□); 2 bar (◇); 3 bar (△)



**ESI Figure 2** Oxidation of cinnamyl alcohol under different oxygen pressure carried out in the presence and absence of the catalyst. Selectivity to cinnamaldehyde and benzaldehyde as a function of oxygen pressure. Reaction conditions: time, 4 hours; 1%AuPd/TiO<sub>2</sub> (Imp), 10 mg; oxygen pressure, 1-3 bar; temperature, 120 °C; 0.5 M cinnamyl alcohol in toluene. **Full figures-** reactions carried out in the absence of the catalyst: CinnALD (■); BenzALD (●); BenzACID (▲); **empty figure-** reactions carried out in the presence of the catalyst: CinnALD (□), BenzALD (○); BenzACID (△)