

This is an Open Access document downloaded from ORCA, Cardiff University's institutional repository:<https://orca.cardiff.ac.uk/id/eprint/130846/>

This is the author's version of a work that was submitted to / accepted for publication.

Citation for final published version:

Alharbi, Reem, Li, Zhibo , Allford, Craig P. , Shutts, Samuel , Krysa, Andrey B. and Smowton, Peter 2020. Design and realisation of InP mode-locked lasers emitting in the 730nm wavelength range [Abstract]. Presented at: Novel In-Plane Semiconductor Lasers XIX, San Francisco, CA, USA, 3-6 February 2020.

Publishers page:

Please note:

Changes made as a result of publishing processes such as copy-editing, formatting and page numbers may not be reflected in this version. For the definitive version of this publication, please refer to the published source. You are advised to consult the publisher's version if you wish to cite this paper.

This version is being made available in accordance with publisher policies. See <http://orca.cf.ac.uk/policies.html> for usage policies. Copyright and moral rights for publications made available in ORCA are retained by the copyright holders.



Design and realisation of InP Modelocked Lasers Emitting in the 730nm Wavelength Range

Reem Alharbi¹, Zhibo Li¹, Craig P. Allford¹, Sam Shutts¹,
Andrey B. Krysa², Peter M. Smowton¹

¹EPSRC Future Compound Semiconductor Manufacturing Hub, School of Physics and Astronomy, Cardiff University, Cardiff, UK

²EPSRC National Centre for III-V Technologies, University of Sheffield, Sheffield, S1 3JD

Short pulse lasers are required for small footprint, low cost and on chip alternatives to the Ti: Sapphire laser and specifically for applications in two-photon fluorescent imaging. We explore the design of InP quantum dot mode-locked lasers (MLL) emitting in the visible to near infrared region and demonstrate performance in a simple two-section monolithic footprint.

The laser structures were grown by MOVPE on n-GaAs (100) substrates oriented 10° off toward <111>. Self-assembled InP QDs were covered by slightly tensile strained GaInP quantum wells and separated by AlGaInP barriers, with AlInP cladding layers forming the remainder of the waveguide. Broad-area oxide-stripe non-lasing segmented contact devices were fabricated to measure the material optical gain and modal absorption spectra, via the segmented contact method. These measurements are used to design the mode locked structures, and in particular the absorber to gain length ratios and also the total cavity length.

The mode locked lasers are fabricated as 10 μm wide ridge waveguides and planarised with BCB. Devices with total cavity length between 2mm and 3.5mm, with uncoated cleaved facets, and saturable absorber (SA) sections representing approximately 20% of the total cavity length have been examined and found to either Q-switch, mode lock or both depending on operating regime (laser current, absorber reverse bias and heat sink temperature).

Short abstract:

We explore the design of InP quantum dot mode-locked lasers (MLL) emitting in the visible to near infrared region by measuring the modal absorption under reverse bias and the modal gain. We demonstrate modelocking performance in a simple two-section monolithic footprint. Devices are characterised as a function of laser current, absorber reverse bias and heat sink temperature and pure Q-switching, pure mode-locking or mixed q-switching / mode locking is obtained depending on operating regime.