

This is an Open Access document downloaded from ORCA, Cardiff University's institutional repository: <https://orca.cardiff.ac.uk/id/eprint/174021/>

This is the author's version of a work that was submitted to / accepted for publication.

Citation for final published version:

Chhabria, Vikesh, Zhou, Zhengyuan and Forbes, Robert 2024. Taylor dispersion analysis as a tool for size measurement of PAMAM dendrimers: the effect of generation, functionality and pH†. *Analytical Methods* 10.1039/D4AY01769B

Publishers page: <http://dx.doi.org/10.1039/D4AY01769B>

Please note:

Changes made as a result of publishing processes such as copy-editing, formatting and page numbers may not be reflected in this version. For the definitive version of this publication, please refer to the published source. You are advised to consult the publisher's version if you wish to cite this paper.


This version is being made available in accordance with publisher policies. See <http://orca.cf.ac.uk/policies.html> for usage policies. Copyright and moral rights for publications made available in ORCA are retained by the copyright holders.



Analytical Methods

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: V. Chhabria, Z. Zhou and R. Forbes, *Anal. Methods*, 2024, DOI: 10.1039/D4AY01769B.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.

ARTICLE

TAYLOR DISPERSION ANALYSIS AS A TOOL FOR SIZE MEASUREMENT OF PAMAM DENDRIMERS: THE EFFECT OF GENERATION, FUNCTIONALITY AND PH

Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

Vikesh Chhabria,^{*a} Robert Forbes^b and Zhengyuan Zhou^c

Taylor Dispersion Analysis (TDA) is explored to measure the hydrodynamic sizes of full and half generation PAMAM dendrimers up to generation 4.5 in various buffer solutions. A method was used to minimize the interaction between the capillary and cationic dendrimers. The effect of generation, surface functionality, pH and ionic strength on the hydrodynamic radii of PAMAM dendrimers were investigated. Our results show that TDA can accurately measure the sizes of PAMAM dendrimers with relatively low standard deviation especially for half generations. It was found the ionisation of functional groups at various pHs led to a conformational change due to electrostatic repulsion or back-folding of the branches. Furthermore, adding salt to a half-generation dendrimer (G4.5) can lead to a profound size change which is dependent on ionic strength. A 17% increase in the size of the G4.5 dendrimer was observed in a 1M NaCl solution compared to that in a 0.1M solution. Compared to dynamic light scattering, TDA is more reliable and tolerant to large particles in the solutions. The findings of this study indicate that TDA could serve as a viable alternative technique for assessing dendrimer size and conformation, as well as studying their binding behavior.

1. Introduction

Pharmaceutical companies are investing heavily in nanotherapeutics to address challenges related to drug solubility, bioavailability, biodistribution, and mimicry. Recent years have seen the transition from bench to market of formulations such as Doxil[®], DaunoXome[®], Oncaspar[®], Feridex[®], and NanoTherm^{®1}. Dendrimers are a class of nanotherapeutics that have shown to overcome certain barriers to drug development such as improving drug solubility, ability to carry the drug across cell membranes and to mimic the in vivo environment². Dendrimers have attracted considerable interest owing to their unique structural and physicochemical properties³. These macromolecules possess a globular shape with internal cavities, exhibit narrow molecular weight distribution, and offer controllable peripheral surface functionality. Such characteristics facilitate drug incorporation through either encapsulation within the internal cavities or surface binding to the functional groups on the periphery, thereby enhancing their utility in drug delivery applications⁴. Now that dendrimer-drug conjugates are entering clinical trials, regulators and industrialists are keen to identify critical quality attributes and have robust methods of their measurement. Recently the challenges of meeting the prescient needs for in-

depth characterisation of drug-dendrimer conjugates have been comprehensively addressed in the literature⁵.

Despite the synthesis of numerous dendrimers with diverse structures over the years, PAMAM dendrimers, as the pioneering commercially available dendrimer family, continue to be the most extensively studied, attributed to their outstanding attributes in pharmaceutical applications³. PAMAM dendrimers have shown potential for e.g. cancer diagnosis and treatment⁶, delivery of immunosuppressives⁷, prophylaxis of eye infections⁸, and transdermal delivery of ketoprofen⁹. Size measurement of PAMAM dendrimers is essential for understanding their structural properties and optimising their performance in various applications. Although such techniques as molecular dynamics simulations, small angle X-ray scattering (SAXS) and small angle neutron scattering (SANS)¹⁰⁻¹² etc. have been employed to characterize PAMAM dendrimers and provide useful insight into dendrimer structure and conformation, challenges remain in accurately measuring the size of PAMAM dendrimers, including the difficulty in characterising small dendrimer sizes, the influence of solvent and environmental conditions on dendrimer conformation, and the need for improved data analysis algorithms and standards for comparison between techniques. These analytical techniques face limitations in sizing dendrimers¹³⁻¹⁸, often due to their specialized requirements and complexities, demanding strict method development and sample preparation. Moreover, they often entail lengthy analysis times and may not fully replicate real experimental conditions, potentially resulting in discrepancies with measurements in actual solutions.

Recently Taylor Dispersion Analysis (TDA) has been applied by several research groups to measure the size of nanomaterials, e.g. inorganic gold and super-paramagnetic nanoparticles¹⁹⁻²¹ and lipid-nanoparticle formulations for mRNA vaccines²². Cottet and coworkers first explored using TDA to measure the diffusion coefficients and hydrodynamic radii of Poly-L-lysine dendrigrafts²³,

^a School of Biosciences, Sir Martin Evans Building, Cardiff University, Cardiff, CF10 3AX. Email: ChhabriaV2@cardiff.ac.uk, vikeshc@gmail.com

^b School of Pharmacy and Biomedical sciences, Maudland building, University of Central Lancashire, Preston, Lancashire PR1 2HE

^c School of Pharmacy and Biomedical sciences, Maudland building, University of Central Lancashire, Preston, Lancashire PR1 2HE.

† Electronic Supplementary Information available: See DOI: 10.1039/x0xx00000x

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Downloaded on 12/17/2024 9:48:12 AM
This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.



They also used TDA to monitor the functionalization by click chemistry of dendrigraft polylysine²⁴ and successfully used TDA to monitor the impact of buffer compositions and ionic strength (e.g. phosphate ions) on the size of linear polylysines²⁵. Comparison was made to the data obtained from dynamic light scattering and size exclusion chromatography. Higher generations showed notable differences in size measurements, mainly due to aggregate contributions to light scattering intensity. TDA was concluded to be the most appropriate technique for evaluating hyperbranched macromolecules. Full generation L-lysine dendrimers up to G6 with ammonium trifluoroacetate and boc-protected surface were prepared and characterized by TDA and size exclusion chromatography to accurately measure various properties including hydrodynamic radii²⁶. These experimental techniques were combined with molecular dynamics simulations to gain insight into the dendrimer structure.

Although Taylor Dispersion Analysis (TDA) has been shown to offer structural insights for several dendrimers in previous studies^{5,26}, there is a lack of extensive reports utilising TDA to measure the sizes of PAMAM dendrimers with diverse surface functionalities. Moreover, investigations into the effects of pH and ionic strength on the conformational changes of dendrimer structures in real solutions are limited. Such studies could enhance our understanding of dendrimer interactions with guest molecules, such as drugs or proteins, and inform the design of dendrimer-based formulations with optimized binding and release behaviour. To address this, we investigated the characterisation of low-generation PAMAM dendrimers (full or half) with various surface functionalities using TDA in conjunction with dynamic light scattering (DLS). The size and conformation changes of dendrimers in various buffer solutions upon ionisation of functional groups were monitored and the effect of counterions and ionic strength on dendrimer size was also investigated.

2. Material and Methods

2.1 Materials

PAMAM dendrimers (G1.5, G3.5, and G4.5, half generation) were purchased from Dendritech Ltd. Full generation PAMAM dendrimers (G3 and G4), Hellmanex III, L-tryptophan, caffeine, DEAE-dextran hydrochloride, sodium acetate trihydrate, acetic acid, sodium hydroxide, 0.22 μm PVDF membrane filter, 1M hydrochloric acid, carbonate buffer, Sodium phosphate dibasic heptahydrate and Sodium phosphate monobasic monohydrate were purchased from Sigma-Aldrich Ltd (Poole, UK).

2.2 Taylor Dispersion Analysis

A Viscosizer 200 (VS200) was used (Malvern Instruments, Malvern, UK) with a Malvern fused silica capillary. Dimensions: 75 μm i.d. 200 μm o.d. with a total length of 130 cm. It can also be possible to determine the capillary i.d. Optically²⁷. The length to window 1 is 45 cm and to window 2 is 85 cm, respectively. The instrument was set to a constant oven and tray temperature of 25.0 °C. Each series of runs were carried out using an optical filter at 214 nm. The instrument was calibrated by stray light corrections using an appropriate stray light test solution 10 mg cm⁻³ L-tryptophan dissolved in water.

2.3 Hydrodynamic Radius measurements of PAMAM Dendrimers

Measurements of hydrodynamic radius (Rh) were conducted using a well-established method which was optimized for full generation dendrimers, so that Rh of PAMAM dendrimers were analysed accurately, with minimal interference by the capillary walls²⁸. The samples were run in triplicate according to the schedule shown in Table 1. Prior to running the PAMAM dendrimer samples, a 1 mg cm⁻³ caffeine standard solution was analysed for Rh (Fig. S1†) to assess the accuracy and repeatability of the instrument. The Analytical instrument utilizes UV imaging and TDA for determining diffusion coefficients and hydrodynamic radii of dendrimer in solution. The UV detector monitors band broadening of the dendrimer solution injected into a stream of buffer solution, driven by a pump through a fused-silica capillary. The dendrimers are imaged at two windows. This band broadening phenomenon is calculated from absorbance versus time data, using the peak times at the first (t1) and second window (t2), and standard deviations τ1 and τ2, using the equation shown below:

$$R_h = \frac{4k_B T (\tau_2^2 - \tau_1^2)}{\pi \eta r^2 (t_2 - t_1)}$$

Where Rh is the hydrodynamic radius; k_B is the Boltzman constant; η is the viscosity of run buffer; r is the radius of the capillary; T is the temperature; t1 and t2 correspond to peak centre times at window the first and second window, and the corresponding standard deviations, τ1 and τ2 (band broadening).


Table 1 Sequence for PAMAM dendrimer measurement.

Injection	Sequence	Pressure (mbar)	Time (min)
1	Rinse (run buffer)	2000	1.00
2	Fill (run buffer)	2000	1.00
3	Reset baseline	140	1.00
4	Load (sample)	140	0.20
5	Dip (run buffer)	0	0.15
6	Run (run buffer)	140	Auto

PAMAM dendrimers samples (G1.5, G3, G3.5, G4 and G4.5) were prepared as 1%w/v in buffers at various pHs and then filtered once before TDA measurement. The samples were measured using the corresponding buffer solutions as the run buffer: 0.067M phosphate (pH 7.4, ionic strength 0.168M), 0.085M hydrochloric acid (pH 1.2, ionic strength 0.135M) and 0.05M carbonate buffer (pH 10.6, ionic strength 0.132M), which allowed investigating the effect of pH on the size, conformation and stability of the dendrimers under stressful environments. G1.5, 3.5, 4.5 dendrimer samples were measured using an uncoated fused silica capillary, which carried an overall negative charge. The half-generation dendrimers carry an overall negative charge and thus had no interaction with the wall of the capillary due to a repulsion effect. In addition, to assess the effect of ionic strength of half-generation dendrimer, 1%w/v dendrimer solutions were prepared by dissolving G4.5 dendrimer in PBS buffer with 0.1 and 1M sodium chloride solutions. The size was measured by the method above. The viscosities of the run buffers were determined by TDA and used for calculation of hydrodynamic radius of the dendrimers under various conditions. The viscosities of the

three buffer solutions are similar to that of water (0.890 cP) due to their low concentrations while the viscosities with 0.1 and 1M

sodium chloride are 0.899 and 0.972 cP, respectively. However, the full-generation dendrimers (G3 and G4) carry an overall positive charge and interact with the walls of the capillary creating a tailing



Scheme 1. Schematic representation of the charges on the capillary wall before and after coating (Scheme 1), and its effect on full generation PAMAM dendrimers with respect to the taylorgram.

unreliable results. To avoid this, we employed a semi-permanent dextran coating to immobilize the charges on the capillary walls.

2.4 Capillary pre-coating with Dextran

In order to coat the capillary wall with dextran, a 25 mM sodium acetate buffer was prepared and adjusted to pH 5.5 using 1M sodium hydroxide, to a final volume of 200 mL. A 2% w/v DEAE dextran solution was prepared in 10 mL sodium acetate buffer. This mixture was filtered through a 0.45 μm nylon membrane filter. The capillary coating was obtained by washing the capillary with 1M sodium hydroxide, which activates the capillary surface. The 2% w/v DEAE dextran solution was then applied to the walls of the capillary. The coating was applied by the method shown in Table 2.

Table 2 Sequence for semi-permanent Dextran coat

Schedule 1			
Injection	Sequence	Pressure (mbar)	Time (min)
1	Water	3000	5.00
2	1M NaOH	3000	5.00
3	water	3000	5.00
Schedule 2			
1	Sodium acetate	3000	1.00
2	2% (w/v) Dextran	3000	10.00
3	Sodium acetate	0	10.00
4	Sodium acetate	3000	2.00

2.5 Capillary washing procedure

The fused silica capillary was washed according to a well published study²⁹. Hellmanex III (2% v/v), a surfactant solution was flushed for 10 minutes at 2000 mbar to wash the capillary after each run and then followed by a wash with water. At times, the capillary was also flushed with nitrogen gas to remove any blockages.



2.6 Dynamic Light Scattering

Size analysis of PAMAM dendrimers was conducted using dynamic light scattering (Zetasizer Nano, Malvern Instruments, UK). The same batch of dendrimer samples for TDA measurement were analysed by DLS without further filtration to compare the results of these two techniques. The dendrimer solutions (1 % w/v) in phosphate buffer (0.067M, pH 7.4), hydrochloric acid buffer (0.085M, pH 1.2), and carbonate buffer (0.05M, pH 10.6) were filtered through a PVDF filter (Millipore, 0.22 μ m pore size) into a clean scattering cell. The measurement was conducted in triplicate.

3. Results and Discussion

3.1 Measurement of Hydrodynamic Radii of Half and Full generation Dendrimers

In this work we explored the size measurement of PAMAM dendrimers using TDA. To ensure accurate and reliable measurement of samples, a 1 mg cm⁻³ caffeine standard was run multiple times to assess the state of the VS200 TDA analyser. As compared to studies by the same group²⁹⁻³¹, the Rh of caffeine shown in Fig. S1[†] was within the range of 0.40-0.42 nm. The sizes of PAMAM dendrimers measured by TDA was assessed by the repeatability of the samples and in reference to the values reported by other techniques³⁴.

The divergent synthesis of PAMAM dendrimers involves a two-step reaction: Michael addition of methyl acrylate to amino groups, followed by amidation of the esters with ethylene diamine. An amine-terminated full generation dendrimer is produced for one complete synthesis cycle. However, if the amidation step is omitted, a half generation dendrimer terminated with carboxyl groups will be formed. A range of lower generation PAMAM dendrimers (full and half generations) were selected for TDA measurements and the effect of pHs on the conformation was investigated in different buffer solutions. The pKa values of full generation PAMAM dendrimers are 7-9 for primary amine groups on the surface and 3-6 for interior tertiary amine groups³¹. For half generation dendrimers, the pKa for surface carboxyl groups is estimated to be around 3 which is a common value for carboxylic acids. Compared to higher generation dendrimers, lower generation dendrimers have relatively-open structure and less dense-packed surface³.

Since the wall of the TDA fused silica capillary is negatively charged, half generation G4.5 PAMAM dendrimer was initially measured by TDA. G4.5 PAMAM dendrimer carries negative charges under neutral or basic conditions due to carboxyl surface groups. The repulsion between G4.5 dendrimer and the walls of the capillary was preferred and therefore the dendrimer did not interact with the capillary walls. Fig. 1a shows a standard TDA profile of a 1%w/v G4.5 dendrimer with a hydrodynamic radius of 2.67 nm (\pm 0.06). As shown in Fig. 1b, the same sample was run in triplicates, and each Taylorgram fit the previous run perfectly, displaying the repeatability of the technique. The positively charged full generation PAMAM dendrimers had minor interactions with the capillary wall and showed a tailing effect in Fig. S2[†], which obviously results in a relatively higher variation in the measurement. However, this interaction was reduced by the presence of a dextran coat that neutralized the surface of capillary wall.




Fig. 1 (a) TDA profile for a 1%w/v G4.5 PAMAM dendrimer solution in phosphate buffer (pH 7.4) recorded at 214nm, showing first and second passes at window 1 and 2. (b) TDA profile showing an overlay of three runs for a 1%w/v G4.5 PAMAM dendrimer solution in PBS (n=3).


As shown in Table 3, a range of PAMAM Dendrimers G1.5, G3.5, G4.5, G3 and G4 were analysed by TDA under various buffer solutions: phosphate (pH 7.4), carbonate (pH 10.6) and HCl (pH 1.2). The measurement of Rh was conducted in three separate runs and showed minute differences with relatively small standard deviations. Various pHs were employed to facilitate monitoring the effect of ionisation of the functional groups on the conformation of dendrimers. Our data show that under the same pH, the Rh increases with the generation of dendrimer, e.g. the Rh values of G1.5, G3.5 and G4.5 dendrimers at pH 7.4 are 1.36, 2.32, 2.67 nm, respectively. This correlation is in agreement with other studies using SAXS, SANS and Molecular dynamics^{13,15,34,35}. This increment in size is mainly attributed to an increase of the focal points within the branches, leading to additional layers of the dendrimer.



Table 3 Hydrodynamic radius of PAMAM dendrimers measured by TDAView Article Online
DOI: 10.1039/D4AY01769B

Sample (1% w/v)	pH	R_h (nm)			Average R_h (nm)
		1	2	3	
G1.5	7.4	1.31	1.36	1.41	1.36 (± 0.05)
	1.2	1.06	1.07	1.10	1.08 (± 0.02)
G3.5	7.4	2.26	2.32	2.37	2.32 (± 0.06)
	1.2	1.61	1.55	1.64	1.60 (± 0.04)
G4.5	7.4	2.73	2.70	2.61	2.67 (± 0.06)
	1.2	1.85	1.89	1.87	1.87 (± 0.02)
G3	7.4	2.23	2.20	2.10	2.18 (± 0.07)
	10.6	2.21	2.27	2.57	2.35 (± 0.19)
	1.2	1.98	2.57	2.12	2.23 (± 0.31)
G4	7.4	2.40	2.64	2.77	2.60 (± 0.19)
	10.6	2.24	2.82	2.45	2.50 (± 0.30)
	1.2	2.62	2.74	2.63	2.66 (± 0.07)

Compared to pH 7.4, there is a significant decrease in the average R_h of the half generation PAMAM dendrimers at pH 1.2 (Fig. 2). However, the degree of reduction in R_h varies amongst each generation. Despite efforts by various research groups³⁵, half-generation PAMAM dendrimers remain inadequately characterized. The structure of charged half-generation dendrimers are expected to be more expanded due to Coulombic repulsion on the surface of the dendrimers and also to an increased solvent cage effect, in which the charged groups were surrounded and stabilized by the solvents while the movement of branches were restricted. Hence under acidic conditions (pH 1.2), the surface carboxyl moieties of half generation dendrimers become neutralized while the interior tertiary amines are protonated. This reduces the repulsion of dendrimer surface and leads to possible back folding of the dendrimer branches, especially for lower generation dendrimers having an open structure. It was observed that TDA enabled a repeatable size measurement of the G1.5 dendrimer at pH 1.2, yielding a size of approximately 1.08 nm. This measurement is particularly noteworthy as it approaches the lower detection limits of conventional techniques, such as light scattering, which often struggle to accurately measure such small particle sizes due to their inherent sensitivity and resolution constraints. This highlights the potential of TDA in providing precise size determinations for very small dendrimer molecules under challenging conditions.

**Fig. 2** Comparison of hydrodynamic radii of PAMAM dendrimers at various pHs measured by TDA.

The effect of pHs on the conformation of full generation PAMAM dendrimers is ambiguous. The conformational behaviour of full generation PAMAM dendrimers was investigated using molecular dynamics simulation¹³, SAXS and SANS^{10,36}. It was found that the radius of gyration of the dendrimers was pH dependent due to electrostatic repulsion between protonated dendritic branches or back-folding of the neutralized surface. In contrast, several studies also reported that the dendrimer size is essentially insensitive to the pH change of the solvent by measuring G4 and G8 PAMAM dendrimers under various pHs using SANS^{11,37}. Further simulation work with an optimized method suggested a pH-induced conformational changes for G4 dendrimer from a 'dense core' at high pH to a 'dense shell' at low pH without significant size swelling¹⁸. In our work, as shown in Fig. 2, no significant difference of R_h was found under various pH conditions for either G3 or G4 dendrimer. G4 dendrimers exhibit a slightly expanded structure at pH 1.2 which may be due to the repulsion effect of the protonated surface and tertiary amine groups. Under basic conditions, the surface amine moieties



are mainly neutralized and less electrostatic repulsion was expected, which leads to a relatively-compact structure and back-folding of surface branches. For G3 dendrimers, the hydrodynamic radii are very similar in different buffer solutions. This is probably due to the smaller size and cavity structure of G3 that leads to less apparent size change with pH.

3.2 Effect of ionic strength on the size of half-generation dendrimers

PAMAM dendrimers are polyelectrolytes due to their multi-functional surface. The conformational behaviour of dendrimers is considered to be influenced by counterions and ionic strength in solutions. Current literature mainly focus on full generation dendrimers with protonated amino moieties³⁸⁻³⁹. These studies suggest that the solutions of monovalent salt with low concentrations e.g. $\leq 1\text{M}$ NaCl solutions show no change to PAMAM dendrimers with respect to size. In this study, we investigated the effect of ionic strength on the size of half generation PAMAM dendrimer by dissolving G4.5 dendrimer in phosphate buffers with 0.1 and 1 M NaCl (ionic strength 0.268M and 1.168M respectively). As shown in Fig. 3, the hydrodynamic radius of G4.5 in phosphate buffer with 0.1M NaCl was decreased compared to that in phosphate buffer alone. G4.5 dendrimers are polyelectrolyte with carboxylate ions, which is efficiently solvated by water. Like conventional polyelectrolytes e.g., polyacrylic acids⁴⁰, sodium ions added can surround the negative charges on the dendrimer surface, weaken the electrostatic repulsion between the dendrimer branches because of electrostatic shielding, which leads to a relatively compact structure. When the salt concentration increases further, it will push the counterions in the diffusion layer of dendrimer into the absorb layer and thus compress the electric double layer of the surface hydration shell of dendrimer. This results in an increase of unneutralized surface and repulsion between the branches. Hence, the hydrodynamic radius in phosphate buffer with 1M NaCl is larger than that in lower salt concentrations.




Fig. 3 Hydrodynamic radius of G4.5 PAMAM dendrimers in phosphate buffer (pH 7.4) with varying NaCl concentrations, measured by TDA at 25 °C, Error bars represent STDEV (n=3).

3.3 TDA vs DLS

Dynamic Light Scattering has been widely employed to measure hydrodynamic size of nanoparticles and investigate the interaction with the surrounding solvent. DLS is one of the most cost-effective sizing techniques with respect to time and volume²⁹. However, it is limited by its quality of light scattering and requires model fitting to properly analyse the raw data. Furthermore, DLS has very strict requirements for sample preparation and struggles with analysing nanoparticles in complex environments²¹. We analysed the Rh of G4 and G4.5 PAMAM dendrimers using DLS to compare with TDA. The same batch of samples were analysed by both techniques and the results were shown in Table 4. The results indicate that TDA is a superior technique compared to DLS for measuring PAMAM dendrimers, which allows for the easy acquisition of undisturbed data. The DLS technique is intensity-weighted, yielding a harmonic z-average hydrodynamic radius and is highly sensitive to the presence of larger particles in a sample. In contrast, TDA employs a UV detector sensitive to mass concentration, resulting in a weight-average hydrodynamic radius⁴¹. The DLS results have shown the presence of 2 peaks (Intensity PSD), leading to an increased z-average radius. This is probably due to the guest particles or aggregates in the samples despite that careful filtration has been applied. The presence of larger particles observed in the DLS measurements likely represents minor amounts of loosely associated clusters of monomeric PAMAM molecules, a common occurrence in DLS due to the stationary and small sample volume. However, despite using identical samples, these larger particles were absent in the TDA measurements, which offers greater tolerance for sample preparation. Under TDA flow conditions, the loose aggregates of PAMAM dendrimers likely dissociate due to flow dynamics, rendering them undetectable. Moreover, when only considering the smaller peaks from DLS, both techniques yielded hydrodynamic radii within a comparable range.

Table 4 Hydrodynamic radius of PAMAM Dendrimers measured by TDA and DLSView Article Online
DOI: 10.1039/D4AY01769B

Sample (1%w/v)	pH	DLS		TDA	
		Intensity mean peak 1 (nm)	Intensity mean peak 2 (nm)	Intensity Z-average (nm)	Average Rh (nm)
G4	7.4	2.97 (± 0.02)	126.1 (± 2.10)	8.82 (± 0.14)	2.60 (± 0.19)
	10.6	2.86 (± 0.02)	114.5 (± 11.63)	7.31 (± 0.13)	2.50 (± 0.30)
	1.2	2.72 (± 0.11)	121.5 (± 11.27)	3.31 (± 0.46)	2.66 (± 0.07)
G4.5	7.4	2.94 (± 0.02)	89.98 (± 7.08)	4.94 (± 0.10)	2.67 (± 0.06)
	1.2	4.68 (± 0.06)	1867 (± 16.64)	4.17 (± 0.02)	1.87 (± 0.02)

3.4 TDA vs Conventional Sizing Techniques

Apart from DLS, PAMAM dendrimers have been investigated using other well-established techniques such as SAXS¹⁰, SANS¹⁸, Molecular dynamics simulation^{5,36}, gel permeation chromatography (GPC)⁴¹ and differential mobility analyser¹⁷. Table 5 shows the dendrimer sizes at neutral conditions reported by the aforementioned techniques in comparison to the data obtained by TDA. The results by TDA are relatively larger due to the solvation of dendrimers in buffer solution. It must be borne in mind that the types of size information obtained by various techniques differ. SANS and SAXS measure radius of gyration (Rg) while MD simulations provide dynamic sizes depending on the simulation conditions. Differential mobility analyser measures the mobility size in gas state instead of in solvent. GPC with viscosity or light scattering detectors can provide information on dendrimer size and structure in aqueous and organic solvents. SANS and SAXS are the preferred choice presently to experimentally measure the dendrimers size in proper medium^{18,36,42}. However, those techniques are normally expensive and time-consuming, and also requires deuterated solvents for enhanced contrast and lower incoherent scattering. Molecular dynamics simulations are capable of estimating the hydrodynamic radius by taking into account the interactions with the solvent and ions, but it is not experimentally measured in real solution. Nevertheless, in this study, TDA has demonstrated its efficacy as a fast, easily prepared, and cost-efficient method. This suggests its potential as a reliable alternative technique for determining the sizes of dendrimers or hyperbranched macromolecules. Notably, it was able to characterize half-generation PAMAM moieties.

Table 5 Hydrodynamic radii of G3 and G4 PAMAM dendrimers measured by TDA and literature values from other well-established Techniques.

Sample	Literature Values					
	SAXS (Å)*	SANS (Å)*	Molecular dynamics (Å)*	GPC (nm)	DMA (nm)	TDA (nm)
	Rg	Rg	Rg	Rh	Rp	Rh
G3 neutral pH (~7)	15.8 ¹⁰	-	17.2 ¹⁵	1.78 ⁴²	1.54 ¹⁷	2.18
G4 neutral pH (~7)	17.1 ¹⁰	21.58 ¹⁸	21.7 ¹⁵	2.24 ⁴²	1.86 ¹⁷	2.60

4. Conclusions

In summary, this study has demonstrated the efficiency of TDA in sizing various PAMAM dendrimers across diverse buffer solutions. The precision of the results has facilitated the determination of structural insights and revealed the sensitivities of dendrimers to their solution environment. Our findings indicate the utility of TDA as a promising orthogonal sizing method for hyperbranched macromolecules like PAMAM dendrimers. This could be valuable for developing dendrimers as effective carriers for drugs or proteins with customized binding capabilities.

Author contributions

Zhengyuan Zhou: Data Curation, Formal analysis, investigation, writing-original draft, Resources, review & editing. **Robert Forbes:** Conceptualization, investigation, methodology, Project administration, supervision, writing-original draft, review and editing. **Vikesh Chhabria:** Data Curation, Formal analysis, investigation, writing-original draft, Validating, review & editing.



Conflicts of interest

There are no conflicts to declare.

Data availability

The data that support the findings of this study are available in the supplementary section of the paper.

Acknowledgements

This work was financially supported by the University of Central Lancashire under a science research program.

Notes and references

- A. Narain, S. Asawa, V. Chhabria, Y. Patil-Sen, *Nanomedicine* **2017**, *11*, 2677.
- D. P. Otto, M. M. de Villiers, *J. Pharm. Sci.* **2018**, *107*, 75.
- R. Esfand, D. A. Tomalia, *Drug Discov Today* **2001**, *6*, 427.
- D. A. Tomalia, H. Baker, J. Dewald, M. Hall, G. Kallos, S. Martin, J. Roeck, J. Ryder, P. Smith, *Polymer J.* **1985**, *17*, 117.
- S. Sonzini, F. Caputo, D. Mehn, L. Calzolari, S. E. Borgos, A. Hyldbakk, K. Treacher, W. Li, M. Jackman, N. Mahmoudi, M. J. Lawrence, C. Patterson, D. Owen, M. Ashford, N. Akhtar, *Int. J. Pharm.* **2023**, *637*, 122905.
- B. William, R. Shukla, J. Baker (University of Michigan), US 11/503,742, **2007**.
- [7] W. M. Saltzman, T. Fahmy, P. Fong (Yale University), US 7,534,449, **2009**.
- J. K. Fairley, C. P. Barrett, J. R. Paull (Starpharma Pty Ltd.), US 14/427,970, **2015**.
- J. Manikkath, A. Manikkath, G. V. Shavi, K. Bhat, S. Mutalik, *J. Drug Delivery Sci. Technol.* **2017**, *1*, 334.
- P. K. Maiti, T. Çağın, G. Wang, W. A. Goddard, *Macromolecules* **2004**, *37*, 6236.
- W. R. Chen, L. Porcar, Y. Liu, P. D. Butler, L. J. Magid, *Macromolecules* **2007**, *40*, 5887.
- T. J. Prosa, B. J. Bauer, E. J. Amis, *Macromolecules* **2001**, *34*, 4897.
- B. Wang, Y. Sun, T. P. Davis, P. C. Ke, Y. Wu, F. Ding, *ACS Sustain Chem Eng.* **2018**, *6*, 11704.
- Y. Liu, L. Porcar, K. L. Hong, C. Y. Shew, X. Li, E. Liu, P. D. Butler, K. W. Herwig, G. S. Smith, W. R. Chen, *J. Chem. Phys.* **2010**, *132*, 124901.
- P. K. Maiti, B. Bagchi, *J. Chem. Phys.* **2009**, *131*, 214901.
- H. Lee, J. S. Choi, R. G. Larson, *Macromolecules* **2011**, *44*, 8681.
- M. Imanaka, Y. Okada, K. Ehara, K. Takeuchi, *J. Aerosol Sci.* **2006**, *37*, 1643.
- Y. Liu, V. S. Bryantsev, M. S. Diallo, W. A. Goddard, *JACS.* **2009**, *131*, 2798.
- J. Gouyon, A. Boudier, F. Barakat, A. Pallotta, I. Clarot, *Electrophoresis* **2002**, *43*, 2377.
- P. Lemal, A. Petri-Fink, S. Balog, *Anal. Chem.* **2018**, *17*, 1217.
- D. A. Urban, A. M. Milosevic, D. Bossert, F. Crippa, T. L. Moore, C. Geers, S. Balog, B. Rothen-Rutishauser, A. Petri-Fink, *Colloids Interface Sci. Commun.* **2018**, *1*, 29.
- C. Malburet, L. Leclercq, J. F. Cottet, J. Thiebaud, E. Bazin, M. Garinot, H. Cottet, *Gene Ther.* **2022**, *1*, 1.
- H. Cottet, M. Martin, A. Papillaud, E. Souaïd, H. Collet, A. Commeyras, *Biomacromolecules* **2007**, *8*, 3235.
- T. Liu, F. Oukacine, H. Collet, A. Commeyras, L. Vial, H. Cottet. *J. Chromatogr. A*, **2013**, *1273*, 111-116.
- X. Jin, L. Leclercq, N. Sisavath, H. Cottet, *Macromolecules* **2014**, *47*, 5320–5327. View Article Online
DOI: 10.1039/D4AY01769B
- R. M. England, S. Sonzini, D. Buttar, K. E. Treacher, M. B. Ashford, *Polym Chem.* **2022**, *13*, 2626.
- S. Roca, L. Leclercq, C. Somnin, L. Dhellemmes, J. Chamieh, H. Cottet, *Electrophoresis*, **2024**.
- H. Zaman, A. G. Bright, K. Adams, D. M. Goodall, R. T. Forbes, *Int. J. Pharm.* **2017**, *522*, 98.
- W. L. Hulse, R. T. Forbes, *Int. J. Pharm.* **2011**, *411*, 64.
- W. L. Hulse, R. T. Forbes, *Int. J. Pharm.* **2011**, *416*, 394.
- W. L. Hulse, J. Gray, R. T. Forbes, *Int. J. Pharm.* **2013**, *453*, 351.
- X. Wang, L. Guerrand, B. Wu, X. Li, L. Boldon, W. R. Chen, L. Liu, *Polymers* **2012**, *4*, 600.
- D. A. Tomalia, A. M. Naylor, W. A. Goddard III, *Angew. Chem. Int. Edit.* **1990**, *29*, 138.
- T. J. Prosa, B. J. Bauer, E. J. Amis, D. A. Tomalia, R. Scherrenberg, *J. Polym. Sci. Part B Polym. Phys.* **1997**, *35*, 2913.
- P. M. Paulo, J. N. Lopes, S. M. Costa, *J. Phys. Chem. B.* **2007**, *111*, 10651.
- P. K. Maiti, T. Çağın, S. T. Lin, W. A. Goddard, *Macromolecules* **2005**, *38*, 979.
- G. Nisato, R. Ivkov, E. J. Amis, *Macromolecules* **2000**, *33*, 4172.
- Y. Q. Ma, *Soft Matter* **2010**, *6*, 1308.
- H. Lee, *Simulat.* **2012**, *38*, 589.
- H. Markovitz, G. E. Kimball, *J. Colloid Interface Sci.* **1950**, *5*, 115.
- H. Cottet, J.-P. Biron, M. Martin, *Anal. Chem.*, **2007**, *79*, 9066-9073.
- S. Uppuluri, D. A. Tomalia, P. R. Dvornic, *PMSE Preprints* **1997**, *77*, 116.

1
2
3
4
5 **Data availability**

6 The data that support the findings of this study are available in th supplementary section of the paper.
7
8
9
10

11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Open Access Article. Published on 14 November 2024. Downloaded on 11/14/2024 9:48:12 AM.
This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.



Analytical Methods Accepted Manuscript