

This is an Open Access document downloaded from ORCA, Cardiff University's institutional repository: <https://orca.cardiff.ac.uk/id/eprint/93741/>

This is the author's version of a work that was submitted to / accepted for publication.

Citation for final published version:

Crole, David Alexander, Freakley, Simon J., Edwards, Jennifer Kelly and Hutchings, Graham John 2016. Direct synthesis of hydrogen peroxide in water at ambient temperature. *Proceedings of the Royal Society A: Mathematical, Physical and Engineering Sciences* 472 (2190) , 20160156. 10.1098/rspa.2016.0156

Publishers page: <http://dx.doi.org/10.1098/rspa.2016.0156>

Please note:

Changes made as a result of publishing processes such as copy-editing, formatting and page numbers may not be reflected in this version. For the definitive version of this publication, please refer to the published source. You are advised to consult the publisher's version if you wish to cite this paper.

This version is being made available in accordance with publisher policies. See <http://orca.cf.ac.uk/policies.html> for usage policies. Copyright and moral rights for publications made available in ORCA are retained by the copyright holders.



Direct synthesis of hydrogen peroxide in water at ambient temperature

David A. Crole, Simon J. Freakley, Jennifer K. Edwards and Graham J. Hutchings*

Cardiff Catalysis Institute and School of Chemistry, Main Building, Park Place, Cardiff, CF10 3AT, UK

Keywords: Hydrogen peroxide; gold; palladium; green chemistry

Summary

The direct synthesis of hydrogen peroxide from hydrogen and oxygen has been studied using an Au-Pd/TiO₂ catalyst. The aim of this work is to understand the balance of synthesis and sequential degradation reactions using an aqueous, stabiliser-free solvent at ambient temperature. The effects of the reaction conditions on the productivity of hydrogen peroxide formation and the undesirable hydrogenation and decomposition reactions are investigated. Reaction temperature, solvent composition and reaction time have been studied and indicate that when using water as the solvent the hydrogen peroxide decomposition reaction is the predominant degradation pathway, which provides new challenges for catalyst design which has previously focused on minimising the subsequent hydrogenation reaction. This is of importance for the application of this catalytic approach for water purification.

Introduction

Hydrogen peroxide (H₂O₂) is a significant commodity chemical with an annual usage now exceeding 3 million tonnes per annum and increasing(1). H₂O₂ is used in a number of selective oxidation processes, such as the synthesis of propene oxide from propene and H₂O₂(2), and also non-synthetic applications which make use of its oxidative properties such as cleaning and bleaching. The existing indirect anthraquinone process for producing H₂O₂ is highly optimised to give high H₂ selectivity towards H₂O₂, however, it only proves to be economically viable when operated at a large scale, typically 10⁵ tons/annum, and hence production currently has to be centralised. Due to this, H₂O₂ is transported to the point of use in a high concentration aqueous solution with added stabilisers, necessitating dilution and potentially removal of stabilisers for it to be effective for many uses, particularly bleaching applications when it is used in very dilute form (3-8 vol%)(3).

The ability to produce H₂O₂ at a desired concentration at the point of use could prove to be a green and economical process. This could potentially be achieved via the direct synthesis of H₂O₂ from oxygen and hydrogen to localise the supply of H₂O₂. Whilst a conceptual simple reaction unfortunately the formation of water is thermodynamically preferred and so the design of the catalyst for the synthesis reaction is of prime importance. Monometallic Pd catalysts have been extensively studied for this reaction(3-5), however, these catalysts can hydrogenate H₂O₂ if no acid or halide stabilisers are present. Hutchings and co-workers found that Au-Pd catalysts are selective and productive, even in the absence of promoters such as acid and halides(6).

*Author for correspondence (Hutch@cardiff.ac.uk).

†Present address: Cardiff Catalysis Institute and School of Chemistry, Main Building, Park Place, Cardiff, CF10 3AT, UK

Various solvents, generally consisting of water and/or alcohols, in combination with acid and/or halide promoters, have been used for the heterogeneously catalysed direct synthesis of H₂O₂. We have extensively reported experiments using a methanol and water mixture in an approximate 2:1 ratio, generally in the absence of acid or halides(1, 6, 7). Lunsford and co-workers utilised a water or ethanol solvent with the addition of chloride, bromide, hydrochloric acid and sulphuric acid promoters(8-11). Choudhary and co-workers utilise an acidic aqueous medium (sulphuric or phosphoric acid), in most cases with one or more halide promoter(12-21). Park and co-workers use a solution of methanol with dissolved NaBr(22-32). Biasi and co-workers generally use methanol in the absence of promoters(33-39), but have also used acidified, bromide-promoted aqueous solutions(40). There are, however, limited studies on the aqueous direct synthesis of H₂O₂ in the absence of promoters.

If the generation of H₂O₂ in aqueous solution without additives becomes viable, it would negate the necessity for the extraction of synthesised H₂O₂ from the anthraquinone process solvents. Furthermore, the removal of stabilisers (as with anthraquinone process produced H₂O₂) or promoters (as may be necessary for H₂O₂ produced by acid or halide promoted direct synthesis) would not be required. The ability to efficiently generate H₂O₂ in a water stream also presents opportunities for water cleaning technologies to be developed. It is this latter application for which there is considerable current interest as H₂O₂ could then have the potential to replace chlorine as a disinfectant for water which would only be possible if stabiliser-free H₂O₂ can be produced in water.

In this work, we examine the effect on the productivity and hydrogenation/decomposition rates of a 2.5% Au 2.5% Pd / TiO₂ catalyst when reaction conditions are moved towards the use of water as a solvent and room temperature reactions. These conditions present a more environmentally friendly and economical reaction compared to previously used conditions(6) as there are no energy demands for heating or cooling and the H₂O₂ requires no further extraction/purification. Using this study to help understand the effect of changing reaction parameters on all processes associated with the direct synthesis of H₂O₂ and identify challenges therein will allow for rational design of catalysts for optimal function in an aqueous / ambient temperature reaction condition.

Experimental

Catalyst preparation

The 2.5 wt% Au-2.5 wt% Pd/TiO₂ catalyst was prepared by wet impregnation of TiO₂ (Degussa, Aeroxide P25). A solution of H₂AuCl₄·3H₂O (1.25 ml, 10g Au/ml, Johnson Matthey), solid PdCl₂ (0.0208 g, Johnson Matthey) and de-ionised water (1 ml) were combined and stirred at 80 °C until the PdCl₂ was completely dissolved. At this point TiO₂ (0.475 g) was added and the mixture continuously stirred and heated until a thick paste was formed. The paste was dried in an oven (110 °C, 16 h), ground to a fine powder and calcined under static air (400 °C, 3 h, 20 °C min⁻¹).

H₂O₂ synthesis, decomposition and hydrogenation

H₂O₂ synthesis, hydrogenation and decomposition experiments were evaluated using a Parr Instruments stainless steel autoclave with a volume of either 100 ml or 50 ml and a maximum working pressure of 14 MPa. To evaluate H₂O₂ synthesis the following reaction conditions were used. The autoclave was charged with catalyst (0.010 g) and solvent (8.5 g HPLC grade H₂O and/or HPLC grade methanol, Fischer Scientific) and sealed. The autoclave was then purged three times with 5% H₂/CO₂ before filling with 5% H₂/CO₂ to a pressure of 2.9 MPa (420 psi) followed by the addition of a further 1.1MPa (160 psi) 25% O₂/CO₂ (both BOC speciality gasses). The reaction mixture was stirred at 1200 rpm at systematically varied reaction times and temperatures. H₂O₂ yield was determined by titrating aliquots of the filtered post-reaction solution with acidified Ce(SO₄)₂ solution (c.a. 0.01 M, Sigma Aldrich) in the presence of Ferroin indicator (c.a. 0.1 ml, Sigma Aldrich).

H₂O₂ hydrogenation and decomposition experiments were carried out with a similar procedure to that of H₂O₂ synthesis experiments but only 420 psi (2.9 MPa) 5% H₂/CO₂ or 420 psi (2.9 MPa) 25% O₂/CO₂ were added to the reactor, respectively. Furthermore, a reaction solvent containing 4 wt% H₂O₂, prepared by the addition of H₂O₂ solution (50 wt%, 0.68 g, Sigma Aldrich) to H₂O (7.82 g), was used. The concentration of H₂O₂ in the reaction solution was accurately

determined before and after the reaction by titrating aliquots of the reaction solution with acidified $\text{Ce}(\text{SO}_4)_2$ in the presence of Ferroin indicator. When a hydrogenation experiment is performed, the measured degree of H_2O_2 degradation represents the sum of both hydrogenation and decomposition processes; thus net hydrogenation can be determined by subtracting the measured decomposition value from the measured total hydrogenation/degradation value, assuming that the reactions happen independently of each other. Aside from the noted differences, reaction parameters are identical to those used for synthesis reactions.

Results and Discussion

In our previous studies on the direct synthesis of H_2O_2 ,^(4, 6, 41) reaction conditions have been standardised to allow differences in H_2O_2 yield to solely reflect differences in catalyst performance. The reaction parameters in these experiments were a 2.9 g H_2O /5.6 g methanol solvent mixture, temperature of 2 °C and a reaction duration of 30 min (gas compositions and pressures identical to those reported in the experimental procedure).⁽⁶⁾ In this work, conditions for the direct synthesis of H_2O_2 are investigated at a range of temperatures and solvent compositions with the aim of understanding how the reaction system affects the balance of H_2O_2 synthesis versus the sequential degradation pathways.

Time on line studies were carried out in the previously utilised H_2O /methanol solvent mixture in addition to H_2O and methanol solvents. Productivity values are reported in figure 1a and show that in each system the productivity is highest at short reaction times as expected when the H_2 concentration will be highest and also the rates of H_2O_2 degradation will be minimal due to the low concentrations of H_2O_2 in the reaction mixtures. Comparing the solvent compositions it is clear to see that the productivity is highest when methanol is used and lowest when H_2O is used across the reaction times investigated. Using Henry's law to compare the solubility of hydrogen in the three solvent compositions shows that hydrogen solubility is around an order of magnitude higher in methanol compared to H_2O , with Henry's constant (H^{cp}) values at 20°C of $9.34 \times 10^{-3} \text{ mol atm}^{-1} \text{ L}^{-1}$ and $8.04 \times 10^{-4} \text{ mol atm}^{-1} \text{ L}^{-1}$ respectively. The amount in ppm of H_2O_2 present in each reaction is shown in figure 1b. We observed that almost all of the H_2O_2 synthesised in the methanol solvent is produced in the first 5 min, whereas in H_2O the maximum H_2O_2 concentration is only attained after 40 min reaction. These observations indicate that the performance of the catalyst in the different solvent compositions is likely to be governed by gas solubility and mass transport effects. The effect of gas solubility can also control the balance of the synthesis / hydrogenation / decomposition pathways in the direct synthesis process shown in scheme 1.

The hydrogenation and decomposition reactions of the different solvent compositions were also studied in an analogous manner using the same catalyst. For the decomposition reaction, figure 2a, it was observed that the relationship between the amounts of H_2O_2 decomposed and time is close to linear for all solvent compositions. It was observed that the least decomposition occurs in the methanol solvent, followed by the H_2O /methanol solvent and the greatest decomposition occurring in the H_2O solvent. These reactions were conducted without the presence of H_2 in the autoclave which indicates the low decomposition rate observed in the methanol solvent is not a result of competitive hydrogenation reactions and in fact H_2O_2 is stabilised in the methanol solvent with respect to the water solvent.

For sequential hydrogenation, figure 2b, we see an inverse of the trend seen for decomposition, with the lowest extent of hydrogenation with respect to time in a H_2O solvent where H_2 solubility will be limited compared to alcohol containing solvent compositions. Methanol and H_2O /methanol solvents appear to have very similar initial rates of hydrogenation, indicating that the addition of 66% methanol to H_2O reduces the mass transport limitations and the catalyst is likely operating in the kinetic regime. The plots for hydrogenation activity tend to plateau at long reaction times; this indicates that after an extended reaction the extent of hydrogenation becomes limited by the availability of hydrogen in solution. These observations indicate that when changing the reaction conditions for the direct synthesis, additional considerations need to be made in terms of catalyst design. If direct synthesis of H_2O_2 is to be successfully achieved in water as solvent, suppressing the decomposition reaction becomes an important factor in catalyst design, not only the suppression of the sequential hydrogenation, as has been the focus of all previous research.

Figure 3 shows an extended study of the solvent effects on the three competing reactions. We observe a maximum measured productivity of H_2O_2 during a 30 min reaction in the 34% H_2O solvent, this is the solvent ratio which has previously been found to be optimal for the Au-Pd / TiO_2 catalyst when tested at 2 °C. Increasing the methanol content of the solvent past this point has little effect on the observed productivity, however it increases the rate of H_2O_2 hydrogenation due to the increased H_2 solubility. The observation that the net H_2O_2 produced remains somewhat constant suggests the fact that the synthesis reaction also increases in proportion to the increased H_2 solubility. These results again highlight the need to design catalysts with reaction conditions in mind. In H_2O rich solvent compositions where H_2 availability is low compared to methanol rich solvent compositions, the hydrogenation and decomposition reactions occur with similar rate ($600 \text{ mol kg}_{\text{cat}}^{-1}$

¹ h⁻¹ net hydrogenation vs 450 mol kg_{cat}⁻¹ h⁻¹ decomposition in an aqueous system) so catalyst design should focus on minimising both reactions equally. In methanol rich solvent compositions the synthesis activity is increased due to the higher H₂ availability but as a consequence so is the H₂O₂ hydrogenation reaction. At this condition the rates of hydrogenation are much higher than the rates of decomposition (790 mol kg_{cat}⁻¹ h⁻¹ net hydrogenation vs 110 mol kg_{cat}⁻¹ h⁻¹ decomposition in a methanol system) suggesting that when working at conditions with high hydrogen availability, deconvoluting the selective and unselective hydrogen activation is most important.

H₂O₂ synthesis productivity and the activity of the two degradation processes, decomposition and hydrogenation, at increasing temperatures are shown in figure 4. Net H₂O₂ productivity was found to decrease significantly with increasing temperature; this is tied to the fact that we see an increase in both degradation processes with increasing temperature. At a temperature of 50 °C we observe for the first time the decomposition rate to be higher than the hydrogenation rate which could be a result of increased thermal decomposition rates of H₂O₂.

Conclusions

Changing the reaction conditions for the direct synthesis of H₂O₂ from the ‘standard’ conditions using methanol/water at 2 °C to ‘aqueous / ambient’ conditions we observe a marked decrease in H₂O₂ yield. This is due in part to increased H₂O₂ degradation that occurs with both an increase in reaction temperature and an increased amount of H₂O in the solvent. The decreased yield is also due to a reduced rate of H₂O₂ synthesis due the reduced H₂ solubility that again occurs with both an increase in temperature and an increased amount of H₂O in the solvent. The concomitant positive effect of reduced H₂ solubility in the ‘aqueous / ambient’ conditions is that the hydrogenation of H₂O₂ is relatively less of a concern than under ‘standard’ conditions. This means that catalysts that are highly active but somewhat unselective due to over hydrogenation under ‘standard’ conditions may prove productive under the ‘aqueous / ambient’ conditions that will be required in water purification applications. It is therefore clear that an improved catalyst design is required to synthesise hydrogen peroxide from H₂ and O₂ in water as solvent at ambient temperature. The main concern to be addressed is the catalyst activity as the catalyst needs to operate with much lower levels of dissolved H₂. To achieve this we consider that catalysts with smaller active nanoparticles could provide the improvement required. In addition, changes in the catalyst formulation should be explored using compositions in which gold, which is not particularly active for the direct synthesis of hydrogen peroxide, is substituted for other components such as tin oxide. (42)

Additional Information

Acknowledgments

We thank Selden Research Limited for financial support for a studentship for David. A. Crole. We thank Peter Woodhead for useful discussions.

Funding Statement

The research has been funded by Selden Research Limited and Cardiff University.

Data Accessibility

Readers can contact opendata@cardiff.ac.uk

Competing Interests

The authors have no competing financial interests.

Authors' Contributions

David A. Crole, Simon J. Freakley, Jennifer K. Edwards and Graham J. Hutchings each provided substantial contributions to conception and design, or acquisition of data, or analysis and interpretation of data, drafting the article or revising it critically for important intellectual content and final approval of the version to be published. The research was directed by Graham J. Hutchings.

References

1. Edwards JK, Hutchings GJ. Palladium and gold-palladium catalysts for the direct synthesis of hydrogen peroxide. *Angewandte Chemie*. 2008;47(48):9192-8.
2. Blanco-Brieva G, Capel-Sanchez MC, de Frutos MP, Padilla-Polo A, Campos-Martin JM, Fierro JLG. New Two-Step Process for Propene Oxide Production (HPO) Based on the Direct Synthesis of Hydrogen Peroxide. *Industrial & Engineering Chemistry Research*. 2008;47(21):8011-5.
3. Samanta C. Direct synthesis of hydrogen peroxide from hydrogen and oxygen: An overview of recent developments in the process. *Applied Catalysis A: General*. 2008;350(2):133-49.
4. Edwards JK, Freakley SJ, Lewis RJ, Pritchard JC, Hutchings GJ. Advances in the direct synthesis of hydrogen peroxide from hydrogen and oxygen. *Catalysis Today*. 2015;248:3-9.
5. Henkel H, Weber W. Manufacture of hydrogen peroxid. US Patent 1,108,752. 1914.
6. Edwards J, Solsona B, Landon P, Carley A, Herzing A, Kiely C, et al. Direct synthesis of hydrogen peroxide from H₂ and O₂ using TiO₂-supported Au-Pd catalysts. *Journal of Catalysis*. 2005;236(1):69-79.
7. Piccinini M, Ntainjua E, Edwards JK, Carley AF, Moulijn JA, Hutchings GJ. Effect of the reaction conditions on the performance of Au-Pd/TiO₂ catalyst for the direct synthesis of hydrogen peroxide. *Physical chemistry chemical physics: PCCP*. 2010;12(10):2488-92.
8. Han Y, Lunsford J. Direct formation of HO from H and O over a Pd/SiO catalyst: the roles of the acid and the liquid phase. *Journal of Catalysis*. 2005;230(2):313-6.
9. Han YF, Lunsford JH. A comparison of ethanol and water as the liquid phase in the direct formation of H₂O₂ from H₂ and O₂ over a palladium catalyst. *Catalysis Letters*. 2005;99(1-2):13-9.
10. Liu Q, Lunsford J. The roles of chloride ions in the direct formation of H₂O₂ from H₂ and O₂ over a Pd/SiO₂ catalyst in a H₂SO₄/ethanol system. *Journal of Catalysis*. 2006;239(1):237-43.
11. Liu Q, Lunsford JH. Controlling factors in the direct formation of H₂O₂ from H₂ and O₂ over a Pd/SiO₂ catalyst in ethanol. *Applied Catalysis A: General*. 2006;314(1):94-100.
12. Choudhary VR, Gaikwad AG, Sansare SD. Activation of supported Pd metal catalysts for selective oxidation of hydrogen to hydrogen peroxide. *Catalysis Letters*. 2002;83(3-4):235-9.
13. Choudhary VR, Samanta C, Gaikwad AG. Drastic increase of selectivity for H₂O₂ formation in direct oxidation of H₂ to H₂O₂ over supported Pd catalysts due to their bromination. *Chemical Communications*. 2004;10(18):2054-5.
14. Choudhary V, Samanta C. Role of chloride or bromide anions and protons for promoting the selective oxidation of H₂ by O₂ to H₂O₂ over supported Pd catalysts in an aqueous medium. *Journal of Catalysis*. 2006;238(1):28-38.
15. Choudhary VR, Samanta C, Choudhary TV. Factors influencing decomposition of H₂O₂ over supported Pd catalyst in aqueous medium. *Journal of Molecular Catalysis A: Chemical*. 2006;260(1-2):115-20.
16. Choudhary V, Jana P. Synergetic effect of two halogen promoters present in acidic reaction medium or catalyst on the H₂O₂ formation (in H₂-to-H₂O₂ oxidation) and destruction over Pd/C (or Al₂O₃) catalyst. *Journal of Catalysis*. 2007;246(2):434-9.
17. Choudhary VR, Samanta C, Jana P. Formation from direct oxidation of H₂ and destruction by decomposition/hydrogenation of H₂O₂ over Pd/C catalyst in aqueous medium containing different acids and halide anions. *Applied Catalysis A: General*. 2007;317(2):234-43.
18. Choudhary VR, Samanta C, Jana P. Hydrogenation of hydrogen peroxide over palladium/carbon in aqueous acidic medium containing different halide anions under static/flowing hydrogen. *Industrial and Engineering Chemistry Research*. 2007;46(10):3237-42.
19. Samanta C, Choudhary VR. Direct formation of H₂O₂ from H₂ and O₂ and decomposition/hydrogenation of H₂O₂ in aqueous acidic reaction medium over halide-containing Pd/SiO₂ catalytic system. *Catalysis Communications*. 2007;8(12):2222-8.
20. Samanta C, Choudhary VR. Direct oxidation of H₂ to H₂O₂ over Pd/CeO₂ catalyst under ambient conditions: Influence of halide ions. *Chemical Engineering Journal*. 2008;136(2-3):126-32.
21. Choudhary VR, Jana P. Direct H₂-to-H₂O₂ oxidation over highly active/selective Br-F-Pd/Al₂O₃ catalyst in aqueous acidic medium: Influence of process conditions on the H₂O₂ formation. *Applied Catalysis A: General*. 2009;352(1-2):35-42.
22. Park S, Jung JC, Seo JG, Kim TJ, Chung Y-M, Oh S-H, et al. Direct Synthesis of Hydrogen Peroxide from Hydrogen and Oxygen Over Palladium Catalysts Supported on SO₃H-Functionalized SiO₂ and TiO₂. *Catalysis Letters*. 2009;130(3-4):604-7.
23. Park S, Kim TJ, Chung Y-M, Oh S-H, Song IK. Direct Synthesis of Hydrogen Peroxide from Hydrogen and Oxygen over Palladium Supported on SO₃H-Functionalized SBA-15. *Catalysis Letters*. 2009;130(3-4):296-300.
24. Park S, Lee S, Song S, Park D, Baeck S, Kim T, et al. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over palladium-exchanged insoluble heteropolyacid catalysts. *Catalysis Communications*. 2009;10(4):391-4.
25. Park S, Seo JG, Jung JC, Baeck S-H, Kim TJ, Chung Y-M, et al. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over palladium catalysts supported on TiO₂-ZrO₂ mixed metal oxides. *Catalysis Communications*. 2009;10(13):1762-5.
26. Park S, Baeck S-H, Kim TJ, Chung Y-M, Oh S-H, Song IK. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over palladium catalyst supported on SO₃H-functionalized mesoporous silica. *Journal of Molecular Catalysis A: Chemical*. 2010;319(1-2):98-107.
27. Park S, Kim TJ, Chung Y-M, Oh S-H, Song IK. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over insoluble Pd_{0.15}M_{2.5}H_{0.2}PW₁₂O₄₀ (M = K, Rb, and Cs) heteropolyacid catalysts. *Research on Chemical Intermediates*. 2010;36(6-7):639-46.
28. Park S, Park DR, Choi JH, Kim TJ, Chung Y-M, Oh S-H, et al. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over insoluble Cs_{2.5}H_{0.5}PW₁₂O₄₀ heteropolyacid supported on Pd/MCF. *Journal of Molecular Catalysis A: Chemical*. 2010;332(1-2):76-83.
29. Park S, Park DR, Choi JH, Kim TJ, Chung Y-M, Oh S-H, et al. Direct

synthesis of hydrogen peroxide from hydrogen and oxygen over palladium catalyst supported on H3PW12O40-incorporated MCF silica. *Journal of Molecular Catalysis A: Chemical*. 2011;336(1-2):78-86.

30. Park S, Choi JH, Kim TJ, Chung Y-M, Oh S-H, Song IK. Direct synthesis of H₂O₂ from H₂ and O₂ over Pd catalyst supported on Cs₂.5H₀.5PW12O40-MCF silica. *Catalysis Today*. 2012;185(1):162-7.

31. Park S, Choi JH, Kim TJ, Chung Y-M, Oh S-H, Song IK. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over Pd/CsXH₃-XPW12O40/MCF (X=1.7, 2.0, 2.2, 2.5, and 2.7) catalysts. *Journal of Molecular Catalysis A: Chemical*. 2012;353-354:37-43.

32. Park S, Lee J, Song JH, Kim TJ, Chung Y-M, Oh S-H, et al. Direct synthesis of hydrogen peroxide from hydrogen and oxygen over Pd/HZSM-5 catalysts: Effect of Brønsted acidity. *Journal of Molecular Catalysis A: Chemical*. 2012;363-364:230-6.

33. Biasi P, Menegazzo F, Pinna F, Eränen K, Canu P, Salmi TO. Hydrogen peroxide direct synthesis: Selectivity enhancement in a trickle bed reactor.

Industrial and Engineering Chemistry Research. 2010;49(21):10627-32.

34. Gudarzi D, Simakova OA, Hernández Carucci JR, Biasi PD, Eränen K, Kolehmainen E, et al. Direct synthesis of H₂O₂ from H₂ and O₂ over carbon supported Au, Pd and Au-Pd/C bimetallic catalysts. *Chemical Engineering Transactions*. 2010;21:925-30.

35. Biasi P, Zancanella S, Pinna F, Canu P, Salmi TO. Hydrogen peroxide direct synthesis: From catalyst preparation to continuous reactors. *Chemical Engineering Transactions*. 2011;24:49-54.

36. Biasi P, Canu P, Menegazzo F, Pinna F, Salmi TO. Direct Synthesis of Hydrogen Peroxide in a Trickle Bed Reactor: Comparison of Pd-Based Catalysts. *Industrial & Engineering Chemistry Research*. 2012;51(26):8883-90.

37. Gemo N, Biasi P, Canu P, Salmi TO. Mass transfer and kinetics of H₂O₂ direct synthesis in a batch slurry reactor. *Chemical Engineering Journal*. 2012;207-208:539-51.

38. Biasi P, Menegazzo F, Canu P, Pinna F, Salmi TO. Role of a Functionalized Polymer (K2621) and an Inorganic Material (Sulphated Zirconia) as Supports in Hydrogen Peroxide Direct

Synthesis in a Continuous Reactor. *Industrial & Engineering Chemistry Research*. 2013;130916123939006.

39. Sterchele S, Biasi P, Centomo P, Canton P, Campestrini S, Salmi T, et al. Pd-Au and Pd-Pt catalysts for the direct synthesis of hydrogen peroxide in absence of selectivity enhancers. *Applied Catalysis A: General*. 2013;468:160-74.

40. Biasi P, García-Serna J, Bittante A, Salmi T. Direct synthesis of hydrogen peroxide in water in a continuous trickle bed reactor optimized to maximize productivity. *Green Chemistry*. 2013;15(9):2502.

41. Edwards JK, Solsona B, N EN, Carley AF, Herzing AA, Kiely CJ, et al. Switching off hydrogen peroxide hydrogenation in the direct synthesis process. *Science*. 2009;323(5917):1037-41.

42. Freakley SJ, He Q, Harray JH, Lu L, Crole DA, Morgan DJ et al., Palladium-tin catalysts for the direct synthesis of H₂O₂ with high selectivity *Science* 2016, 351, 965-968.

Figure and table captions

Figure 1 – Time on line H₂O₂ productivity (a) and yield (b) in water, 34% water / 66% methanol and methanol solvent systems.

■ – Methanol, ● – 34% Water / 66% Methanol, ▲ - Water.

Conditions: Reaction time as indicated, 8.5g solvent, 100 ml autoclave, ambient temperature (20-25°C), 1200rpm, 10mg catalyst, 420 psi H₂/CO₂ + 160 psi O₂/CO₂.

Figure 2 – Time on line H₂O₂ decomposition (a) and net hydrogenation (b) in water, 34% water / 66% methanol and methanol solvent systems.

■ – Methanol, ● – 34% Water / 66% Methanol, ▲ - Water.

Conditions: Reaction time as indicated, 8.5g solvent, 100 ml autoclave, ambient temperature (20-25°C), 1200rpm, 10mg catalyst, 420 psi H₂/CO₂ (a) or 420 psi O₂/CO₂ (b).

Figure 3 – H₂O₂ productivity, decomposition and net hydrogenation as a function of solvent composition.

■ – Productivity, ● – Net Hydrogenation, ▲ - Decomposition.

Conditions: 30 min reaction time, 8.5g solvent as indicated, 50 ml autoclave, 20°C, 1200rpm, 10mg catalyst, 420 psi H₂/CO₂ + 160 psi O₂/CO₂ (productivity), 420 psi H₂/CO₂ (hydrogenation) or 420 psi O₂/CO₂ (decomposition).

Figure 4 – H₂O₂ productivity, decomposition and net hydrogenation in water as a function of temperature in aqueous solvent.

■ – Productivity, ● – Net Hydrogenation, ▲ - Decomposition.

Conditions: 30 min reaction time, 8.5g H₂O solvent, 50 ml autoclave, temperature as indicated, 1200rpm, 10mg catalyst, 420 psi H₂/CO₂ + 160 psi O₂/CO₂ (productivity), 420 psi H₂/CO₂ (hydrogenation) or 420 psi O₂/CO₂ (decomposition).


Scheme 1

Reaction scheme for the direct synthesis of hydrogen peroxide.

Figures

Figure 1

a)



b)





Figure 2

a)



b)




Figure 3





Figure 4



Scheme 1

